

Characterization of ZnO - Biopolymer Nano Composites

Arnab Gangopadhyay and A. Sarkar

Professor, Department of Physics, Bijay Krishna Girls College, India

Abstract

In this work ZnO Nano clusters were grown in biopolymer background. Attempt has made to control the Nano-cluster size by the in situ chemical sol-gel process. The dc volt-ampere characteristics of the developed ZnO Nano composites which were prepared under different conditions were measured. XRD and optical absorption of the material were also studied to get information on grain size. The work indicated a possible new characterization technique by the use of the dc I-V characteristic which perhaps contains information about cluster size of the Nano composites. Zinc oxide powders was prepared via co precipitation and used as inorganic materials; polyvinylalcohol was used as polymer matrix. The technical approach involves the introduction of Nano-particles into polymer matrix whereby Nano-particles has antibacterial characteristics and enhanced inclusion into the polymer matrix.

Keywords

Nano composites, Spectrophotometer, Electrical conduction.

INTRODUCTION

Nano composites (NC) draw attention for their novel properties. ZnO is an eco-friendly material moreover non toxic for human bodies. ZnO NC may be useful in bio-medical applications. ZnO Nano clusters are large band gap semiconductor and they can be produced by various ways. The material is an important in development of solar cells due to their small cluster size (~50nm). Production of NC's via bottom up sol-gel route is cheaper than top down route. In this work ZnO NC were synthesized following low temperature (~100°C) sol-gel route. The process uses zinc acetate as main reagent and gum Acacia as a capping agent. It is important to study the properties and cluster size of a NC sample for better application. The objective of the work aiming at a new characterization technique from the study of dc electrical character the later is legitimate as a quick and easy method compared to other micrographic techniques.

MATERIALS AND METHODS

Sample Preparation: In-situ production of ZnO NC was made from zinc acetate, analytical grade, M.W. 219.50 (product of CDH, India) and gum Arabica (E. Merck Ltd, India) as starting materials. The later is a high potential biopolymer [1]. 100ml M/10 solution of Zn(CH₃COO)₂ in distilled water was drop wise mixed with hot (~100°C) diluted aqueous solution of Acacia while the Acacia solution was vigorously stirred with magnetic stirrer. It was then refluxed for 10 hours. Rates of drops were set at 2 second interval and 4 second interval for two samples (sample 2 and sample 3) respectively. Also a sample (sample 4) with 10ml M/10 Zn (CH₃COO)₂ at 10 second drop interval was prepared through same process. Another sample (sample 1) was made with 100ml M/10 Zn(CH₃COO)₂ solution mixed at a time with Acacia and refluxed for 10 hours.

Measurements: DC I-V characteristics of the developed Nano-composites were measured at 20mV voltage steps (0 to 2V) using PC interfaced Keithley 2400 source meter. Optical absorbance of sample 1 was measured with Systronics 2201 UVVIS spectrophotometer. XRD of ZnO specimens were measured with Rigaku Miniflex, Japan using Cu K α line.

RESULTS AND DISCUSSION

From I-V measurement of sample is observed the typical characteristics of NC which also appear. I/A (where I =measured current, A =sample thickness, A = area of contact) is plotted in vertical axis.

The average slopes of two graphs of Fig.2 are 0.004e-9ohm-1cm-1 and 0.55e-9ohm-1cm-1 respectively. The results of same measurement on sample 3 and 4 are shown in Fig.2 (graph A and graph B respectively) having average slopes 0.003e-9ohm-1cm-1 and 0.007e-9ohm-1cm-1 respectively. It is the hall mark for NC dimension in the non-complex's.

General nature of graphs indicates that samples contain Nano clusters with different sizes. It is apparent that the average NC sizes in the developed Nano-composites are of decreasing magnitude as we pass from sample 1 to sample 4. The results summarized by Fig.1 and Fig.2 show a clear evidence of reduction in average NC sizes by decrease in amplitude of coulomb blockade in the respective dc I-V characteristics.

Using Scherer formula, the estimated average grain size of the ordinary ZnO is 98.39nm whereas ZnO NC has average grain size 42.22nm. It shows the optical absorption spectra of sample 1. ZnO has bulk band gap 3.2eV corresponding to 388.4 nm wavelength. A peak appears at 381nm corresponding to blue shifted band gap 3.26eV due to quantum size effect .

Conclusion

Gum Acacia capped ZnO NC have been prepared successfully. The dc I-V characteristics bear the signature of different NC with probable variation of grain size.

Email: arnabg@yahoo.com