

Opinion

Biochips & Tissue Chips

Open Access

Metallic Nanoparticles-Based Biochip with Multi-Channel for Immunoassay

Yongqi Fu*

School of Physical Electronics, University of Electronic Science and Technology of China, Chengdu 610054, Sichuan Province, P. R. China

Recently, biochemistry nanosensor is an active research topic in both life sciences and engineering [1]. It involves the interdisciplinary areas of life sciences and information sciences such as bioinformatics, biochemistry chip, bio cybernetics, bionics, and bio-computer etc. Their common characteristics are exploring and opening out the basic rules of the production, storage, transmission, process, transition, and control of the information in the biological systems, and discussing the basic methods which are employed for the human economy activity. The biosensor related research focuses on combination of the sensors and the diversified biological active materials as well as their relevant applications.

The Localized Surface Plasmon Resonance (LSPR)-based nanosensor becomes the hotspot problem because they have benign development situation and important position in the life sciences research [2-8]. LSPR nanosensor can be implemented using extremely simple, small, light, robust, and low cost equipments. It has many advantages such as convenience, high sensitivity, wide application and real-time detection etc. Thus it is deemed to be a kind of furthest potential biosensor. The metallic nanoparticles' optical properties mainly depend on their size, shape, metal composition and the refractive index of the surrounding mediums. Previous research has shown that the LSPR-based nanosensor is a refractive index-based sensing device which strongly relies on the extraordinary optical properties of noble (e.g. Ag, Au, Cu, and their alloy) metal nanoparticles [9-12]. The Ag nanoparticles have endowed the device with excellent optical characteristics. Especially, the peak wavelength of the transmittance spectrum $\lambda_{_{max}}$ is unexpectedly sensitive to the nanoparticle's size, shape, and local external dielectric environment, as shown in Figure 1. Its sensitivity to the nanoenvironment has given us the foundation to develop a new serial of nanoscale affinity biochemosensors. In this paper, we used multi-channel optical biochip with different shapes and periods of metallic nanostructure array as the biosensors' substrates to



Figure 1: Metallic nanoparticles-based biochip with multi-channels filled with nanoparticles fabricated in different shapes and sizes, integrated on one chip for immunoassay.



measure the transmission and extinction spectrum of these nanoscale biosensors, as shown in Figure 2. Through the experimental results, we found that these LSPR nanobiosensors with different shapes and periods nanoparticles array can be used as the nanobiosensor. Moreover, multichannel optical biochip can realize detecting the target molecule using different shapes and periods simultaneously. The biochip can be used for two purposes: 1) detecting one bio-sample on the chip in different channels for different analyzing sensitivity; and 2) analyzing multisamples on the chip at one time: high efficient immunoassay.

Fabrication of the multi-channel optical biochip with different shapes and periods of metallic nanostructure array is a challenging issue. Normally, self-organized assembly technique is employed for the particles distributed in large area with pure one shape and size. However, it is too difficult to adopt the technique for the multi-channel chip here unless the particles are fabricated one channel by one channel separately. Of course, it is a tedious fabrication process. The other option is a physical methodology-based fabrication process, such as Focused Ion Beam Direct Milling (FIBM) and e-beam lithography. FIBM is a one-step processing technology, and quite suitable for manufacturing a prototype for research. Considering advantages of writing any shapes of the particles by FIBM and e-beam writing, they provide more freedom for the chip design in comparison to that of the chemical method.

Apparently, the metallic nanoparticles-based biochip with multi-

*Corresponding author: Yongqi Fu, School of Physical Electronics, University of Electronic Science and Technology of China, Chengdu 610054, Sichuan Province, P. R. China, Tel: +86-28-83-20-23; E-mail: yqfu@uestc.edu.cn

Received February 07, 2014; Accepted February 08, 2014; Published February 10, 2014

Citation: Fu Y (2014) Metallic Nanoparticles-Based Biochip with Multi-Channel for Immunoassay. J Biochips Tiss Chips 4: 108. doi:10.4172/2153-0777.1000108

Copyright: © 2014 Fu Y. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Citation: Fu Y (2014) Metallic Nanoparticles-Based Biochip with Multi-Channel for Immunoassay. J Biochips Tiss Chips 4: 108. doi:10.4172/2153-0777.1000108

Page 2 of 2

channel has the advantages of high throughput, high efficiency, and cost effective bioassay. Hopefully, it will appear in hospitals and pharmacy corporations in the near future.

The author thanks Dr. Shaoli Zhu for her help providing the pictures in the full text.

References

- Hicks GP, Updike SJ (1966) The preparation and characterization of lyophilized polyacrylamide enzyme gels for chemical analysis. Anal Chem 38: 726-730.
- Link S, El-Sayed M (1999) Spectral properties and relaxation dynamics of surface plasmon electronic oscillations in gold and Ag nanodots and nanorods. J Phys Chem B 103: 8410-8426.
- Kelly KL, Coronado E, Zhao LL, Schatz GC (2003) The optical properties of metal nanostructures: The influence of size, shape, and dielectric environment. J Phys Chem B 107: 668-677.
- Link S, El-Sayed MA (2003) Optical properties and ultrafast dynamics of metallic nanocrystals. Annu Rev Phys Chem 54: 331-366.
- Jackson JB, Halas NJ (2001) Ag nanoshells: Variation in morphologies and optical properties. J Phys Chem B 105: 2743-2746.
- 6. Malinsky MD, Kelly KL, Schatz GC, Van Duyne RP (2001) Chain length

dependence and sensing capabilities of the localized surface plasmon resonance of Ag nanostructures chemically modified with alkanethiol self-assembled monolayers. J Am Chem Soc 123: 1471-1482.

- Shaoli Z, Fei L, Xiangang L, Chunlei Du, Yongqi F (2008) A Localized Surface Plasmon Resonance Nanosensor Based on Rhombic Ag Nanoparticle Array. Sensors Actuators B Chem 134: 193-198.
- Shaoli Z, Fei L, Xiangang L, Chunlei D, Yongqi F (2008) A novel bio-nanochip based on localized surface plasmon resonance spectroscopy of rhombic nanoparticles. Nanomedicine 3: 669-677.
- Haes AJ, Van Duyne RP (2002) A nanoscale optical biosensor: sensitivity and selectivity of an approach based on the localized surface plasmon resonance spectroscopy of pyramidal Ag nanostructures. J Am Chem Soc 124: 10596-10604.
- Haes AJ, Van Duyne RP (2003) Nanosensors enable portable detectors for environmental and medical applications. Laser Focus World 39: 153-156.
- Riboh JC, Haes AJ, McFarland AD, Yonzon CR, Van Duyne RP (2003) A nanoscale optical biosensor: real-time immunoassay in physiological buffer enabled by improved nanostructure adhesion. J Phys Chem B 107: 1772-1780.
- Haes AJ, Zou S, Schatz GC, Van Duyne RP (2004) A nanoscale optical biosensor: The long range distance dependence of the localized surface plasmon resonance of noble metal nanostructures. J Phys Chem B 108: 109-116.

Submit your next manuscript and get advantages of OMICS Group submissions

Unique features:

- User friendly/feasible website-translation of your paper to 50 world's leading languages
- Audio Version of published paper Digital articles to share and explore

Special features:

- _____
- 300 Open Access Journals
 25.000 editorial team
- 21 days rapid review process
- Quality and auick editorial, review and publication processing
- Indexing at PubMed (partial), Scopus, EBSCO, Index Copernicus and Google Scholar etc
- Sharing Option: Social Networking Enabled
 Authors, Reviewers and Editors rewarded with online Scientific Credits
- Better discount for your subsequent articles
- Submit your manuscript at: www.omicsonline.org/submission

Citation: Fu Y (2014) Metallic Nanoparticles-Based Biochip with Multi-Channel for Immunoassay. J Biochips Tiss Chips 4: 108. doi:10.4172/2153-0777.1000108