

An Overview: Biological Organisms That Serves as Nanofactories for Metallic Nanoparticles Synthesis and Fungi Being the Most Appropriate

Nida Tabassum Khan, Maham Jamil Khan, Jibran Jameel, Namra Jameel and Saad Umer Abdul Rheman

Department of Biotechnology, Faculty of Life Sciences and Informatics, Balochistan University of Information Technology Engineering and Management Sciences, (BUIITEMS), Quetta, Pakistan

Abstract

Nanotechnology implies to the manipulation, reduction and fabrication of materials at nano scale. Nanoparticles, exhibiting distinct morphological characteristics which is quite different from their bulk form. In recent years nanoparticles have been produced by industries for commercial application having many benefits. Biosynthesis of nanoparticles attracts many researchers and industries to explore microorganisms such as Bacteria, Fungi, Algae etc as the perfect biological system for the assembly of different nanoparticles. Fungi being the most suitable as mycosynthesis is not only ecofriendly but also makes the downstream processing for product recovery much easier.

Keywords: Bacteria; Algae; Fungi; Nanoparticles

Introduction

Different metallic nanoparticles are designed by the transformation of their bulk form in to nano scale [1], possessing unique properties with various uses in different fields such as biotechnology, nanotechnology, medicine, biochemistry and material engineering etc. [2]. Further many synthetic approaches being used for the fabrication of metallic nanocrystals, bio-based green methods have been established because it is not only environmental friendly but provides a clean and non-hazardous way for the fabrication of metallic nano sized particles. Bio-based amalgamation of nano particles using microorganisms as nanofactories is an innovative green technology that promises scientific benefits in future [3,4].

Microorganisms as bionanofactories

In recent years nanoparticles have been produced by industries for commercial application having many benefits. Biosynthesis of nanoparticles attracts many researchers and industries to explore microorganisms as the perfect biological system for the production of different nanoparticles. The metabolic activity of these microorganisms enables the extra cellular or intracellular synthesis of nanoparticles utilizing different mode of synthesis [5-8]. Microorganisms possess the capability to minimize the toxicity of metal ions through bio-reduction or by the aggregation of non-soluble complexes with metal ions to produce colloidal particles. In comparison, biologically synthesized nanomaterials are more definite in size than the chemically synthesized ones because of optimized growth of the crystal due to steady reaction kinetics which reduces the overall investment involved in nanoparticle synthesis. Not only reduction in the overall cost makes it less expensive process but also it is an eco- friendly method because it does not apply poisonous chemicals that are expensive and harmful for the environment as used in non-biological synthetic procedures that produces nanoparticles of poor morphology. Therefore nanoparticles of distinct morphology can be obtained through the optimization of culture conditions using biological organisms [9].

An account of organisms responsible for nanoparticle synthesis

Different metal nanoparticles, such as iron, silver, silica, selenium, gold, tellurium, platinum, quantum dots, lead, titanium, zirconium, magnetite, palladium, and silver –gold alloy can be biosynthesised by

viruses, bacteria, fungi, plants and actinomycetes [10]. These organisms possess metal ion reduction capabilities thus making them suitable to be employed for synthesis of nanoparticles.

Bacteria in nanoparticle synthesis

Several bacterial species have been reported to produce metallic nanoparticles of different types. For example Bacteria like *Desulfuromonas acetoxidans*, *Shewanella* spp and *Magnetospirillum magnetotacticum* produces iron oxide nanoparticles [11]. In addition Copper and Cadmium sulfate nanoparticles were produce by photosynthetic bacteria of genus *Serratia* and *Rhodobacter sphaeroides* respectively [12,13] while *Escherichia coli* is reported to produce Cadmium nanocrystals [14].

Plants in nanoparticle synthesis

Not only bacteria but plants can also be used to produce nanoparticles of different types. For example from *Hordeum vulgare* (monocotyledonous) and *Rumex acetosa* (dicotyledonous) plants, iron oxide nanoparticles were produced [15]. In addition to that, *Diopyros kaki* leaf extract is known for the green production of platinum nano crystals [16], gold nanocrystals using *Gnidia glauca* flower extract [17], silver and gold nano crystals from Aloe Vera extract [18] and clove [19] have been reported.

Algae in nanoparticle synthesis

Chlorella vulgaris, unicellular green algae that possess the capability to produce crystalline metal nanoparticles at room temperature. The hydroxyl groups in tyrosine subunits or the carboxyl groups in

***Corresponding author:** Khan NT, Department of Biotechnology, Faculty of Life Sciences and Informatics, Balochistan University of Information Technology Engineering and Management Sciences, (BUIITEMS), Quetta, Pakistan, Tel: 03368164903; E-mail: nidatabassumkhan@yahoo.com

Received March 08, 2017; **Accepted** April 20, 2017; **Published** April 26, 2017

Citation: Khan NT, Khan MJ, Jameel J, Jameel N, Rheman SUA (2017) An Overview: Biological Organisms That Serves as Nanofactories for Metallic Nanoparticles Synthesis and Fungi Being the Most Appropriate. Bioceram Dev Appl 7: 101. doi: [10.4172/2090-5025.1000101](https://doi.org/10.4172/2090-5025.1000101)

Copyright: © 2017 Khan NT, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

S. No	Fungus name	Mechanism	Nanoparticles
1	<i>Fusarium oxysporum</i>	Extracellular	Pt [23]
		Extracellular	Ag [24,25,26]
		Extracellular	CdSe quantum dots [26]
		Extracellular	CdS [27]
		Extracellular	Magnetite [28]
		Extracellular	Si, Ti [29]
		Extracellular	Zirconia [30]
		Intracellular	Au [31]
		Extracellular	Au [32]
		Extracellular	BT [33]
		Intracellular	Zn [34]
2	<i>Verticillium sp.</i>	Intracellular	Au [35]
		Extracellular	Magnetite [28]
		Intracellular	Ag [36]
		Extracellular	Fe ₃ O ₄ [28]
3	<i>Verticillium luteoalbum</i>	Intracellular	Au [37]
4	<i>Phoma sp.</i>	Intracellular	Ag [38]
5	<i>Phoma glomerata</i>	Extracellular	Ag [39]
6	<i>Colletotrichum sp.</i>	Extracellular	Au [40]
7	<i>Coriolus versicolor</i>	Extracellular	Ag [41]
8	<i>Cladosporium cladosporioides</i>	Extracellular	Ag [42]
9	<i>Usnea longissima</i>	Extracellular	Usnic acid [42]
10	<i>Trichothecium sp.</i>	Extra/Intra	Au [43]
11	<i>Trichoderma asperellum</i>	Extracellular	Ag [44]
12	<i>Aspergillus fumigates</i>	Extracellular	Ag [45]
		Extracellular	ZnO [46]
13	<i>Fusarium semitectum</i>	Extracellular	Ag [47]
		Intracellular	Au [48]
14	<i>Aspergillus flavus</i>	Intracellular	Ag [49]
		Extracellular	TiO ₂ [50]
15	<i>Aspergillus niger</i>	Extracellular	Ag [51]
		Extracellular	Au [52]
		Intracellular	Au [52]
16	<i>Fusarium acuminatum</i>	Extracellular	Ag [53]
17	<i>Penicillium sp.</i>	Extracellular	Ag [54]
18	<i>Helminthosporium solani</i>	Extracellular	Au [55]
19	<i>Fusarium solani</i>	Extracellular	Ag [56]
20	<i>Aspergillus oryzae</i>	Extracellular	FeCl ₃ [57]
21	<i>Aspergillus tubingensis</i>	Extracellular	Ca ₃ P ₂ O ₈ [58]
22	<i>Rhizopus oryzae</i>	Cell surface	Au [59]
23	<i>Rhizopus stolonifer</i>	Cell surface	Au [60]
		Extracellular	Ag [61]
24	<i>Aureobasidium pullulans</i>	Intracellular	Au [31]
25	<i>Neurospora crassa</i>	Extracellular	Au [27]
26	<i>Penicillium brevicompactum</i>	Extracellular	Au [62]
27	<i>Cylindrocladium floridanu</i>	Extracellular	Au [63]
28	<i>Phanerochaete chrysosporium</i>	Extracellular	Au [64]
29	<i>Volvariella volvacea</i>	Extracellular	Au [65]
30	<i>Sclerotium rolfsii</i>	Extracellular	Au [63]
31	<i>Coriolis versicolor</i>	Extracellular	Au [66]
		Intracellular	Au [66]
		Extracellular	Ag [41]
		Intracellular	Au [46]

32	<i>Candida albicans</i>	Intracellular	Au [67]
33	<i>Pleurotus sajor caju</i>	Extracellular	Ag [49]
34	<i>Penicillium fellutanum</i>	Extracellular	Ag [68]
35	<i>Penicillium strain J3</i>	Extracellular	Ag [69]
36	<i>Trichoderma viride</i>	Intracellular	Ag [70,71]
		Extracellular	
37	<i>Amylomyces rouxii</i> KSU-09	Extracellular	Ag [72]
38	<i>Aspergillus clavitus</i>	Extracellular	Ag [73]
39	<i>Aspergillus terreus</i> CZR-1	Extracellular	Ag [74]

Table 1: List of different metal nanoparticles produced by fungi.

glutamine/aspartic subunits of the proteins present in the extract are accountable for silver ion reduction and also aids in controlling the definite size of nanosilver crystals [20].

Fungi in nanoparticle synthesis

From a total of 1.5 million species of fungi found on Earth about seventy thousands species have been documented. According to a recent study it was estimated that nearly 5.1 million fungal species are found on Earth by the use of high-through put sequencing methods [21]. Selecting Fungi for mycofabrication purposes is the most pertinent choice because of its high metal ion tolerance and bioaccumulation capabilities [22]. Intra or extracellular mycosynthesis of a number of different metallic nanoparticles have been enlisted in Table 1 [23-74].

Why fungi being the most appropriate?

Using fungal biomass or biomass extracts, for the production of nanoparticles is more advantageous compared with other biological methods because fungi, being abundant in nature can be easily isolated by plating, serial dilutions and hyphal extraction. Culturing/sub-culturing requires simple media nutrients and since they are totipotent therefore spores or hyphae can be used to grow fungus to obtain pure isolate after sub culturing [75, 76]. Besides have the potential to be scaled up for large-scale synthesis by producing large amounts of extracellular enzymes which catalysis the heavy metal ions to produce the respective metallic nanoparticle of definite size and shape. Myco-synthesis offers simple downstream processing for product recovery with easy biomass handling [10], thus making the whole process environmental friendly and cost effective.

Conclusion

Among different biological organisms, Fungi serve as a prime candidate for the production of different nanoparticles because of its high tolerance towards metal ions with reduction capabilities. Above all makes the downstream processing for product recovery easy.

References

- Ahmed M, Karns M, Goodson M, Rowe J, Hussain SM, et al. (2008) DNA damage response to different surface chemistry of silver nanoparticles in mammalian cells. *Toxicol Appl Pharmacol*. 233: 404-410.
- Mubarak Ali D, Sasikala M, Gunasekaran M, Thajuddin N (2011) Biosynthesis and characterization of silver nanoparticles using marine cyanobacterium, *oscillatoria willei* ntdm01. *Nanomater* 6: 385.
- Rai M, Yadav A, Gade A (2008) Current trends in phytosynthesis of metal nanoparticles. *Crit Rev Biotechnol*. 28: 277-284.
- Huang J, Li Q, Sun D, Lu Y, Su Y, et al. (2007) Biosynthesis of silver and gold nanoparticles by novel sundried *Cinnamomum camphora* leaf. *Nanotechnology*. 18: 10.
- Parial D, Patra HK, Dasgupta AKR, Pal R (2012) Screening of different algae for green synthesis of gold nanoparticles. *Eur J Phycol*. 47: 22-29.

6. Chakraborty N, Pal R, Ramaswami A, Nayak D, Lahiri S (2006) Diatom: A potential bio-accumulator of gold. *Radioanal Nucl Chem.* 270: 645–649.
7. Nayak RR, Pradhan N, Behera D (2011) Green synthesis of silver nanoparticle by *Penicillium purpurogenum* NPMF: the process and optimization. *J Nanopart Res.* 13: 3129–3137.
8. Nethradevi C, Sivakumar P, Renganathan S (2001) Green synthesis of silver nanoparticles using datura metel flower extract and evaluation of their antimicrobial activity. *International Journal of Nanomaterials and Biostructures.* 2: 16-21.
9. Vijayaraghavan K, Nalini SPK (2010) Biotemplates in the green synthesis of silver nanoparticles. *biotech j.* 5: 1098–1110.
10. Narayanan KB, Sakthivel N (2010) Biological synthesis of metal nanoparticles by microbes. *Adv Colloid Interface Sci.* 156: 1-13.
11. Abhilash (2011) Microbial synthesis of iron-based nanomaterials: A review. *Bull Mater Sci.* 34: 191-198.
12. Hasan SS, Parikh R, Singh S, Prasad BLV (2008) Bacterial synthesis of copper/copper oxide nanoparticles. *J Nanosci Nanotechnol.* 8: 3191-3196.
13. Huang J, Lin L, Li Q, Sun D, Wang Y, et al. (2008) Continuous-flow biosynthesis of silver nanoparticles by lixivium of Sundried Cinnamomum camphora leaf in tubular microreactors. *Ind Eng Chem Res* 47: 6081–6090.
14. Sweeney RY, Mao C, Gao X, Burt JL, Belcher AM, et al. (2004) Bacterial biosynthesis of cadmium sulfide nanocrystals. *Chemistry & Biology* 11: 1553–1559.
15. Makarov VV, Makarova SS, Love AJ, Sinitsyna OV, Dudnik AO, et al. (2014) Biosynthesis of stable iron oxide nanoparticles in aqueous extracts of *Hordeum vulgare* and *Rumex acetosa* plants. *Langmuir* 30: 5982-5988.
16. Song JY, Kwon EY, Kim BS (2010) Biological synthesis of platinum nanoparticles using *Diopyros kaki* leaf extract. *Bioprocess Biosyst Eng* 33: 159-164.
17. Ghosh S, Patil S, Ahire M, Kitture R, Gurav DD, et al. (2012) *Gnidia glauca* flower extract mediated synthesis of gold nanoparticles and evaluation of its chemocatalytic potential. *J Nanobiotechnology.* 10: 17.
18. Chandran SP, Chaudhary M, Pasricha R, Ahmad A, Sastry M (2006) Synthesis of gold nanotriangles and silver nanoparticles using *Aloe Vera* plant extract. *Biotechnol Prog.* 22: 577-583.
19. Singh AK, Talat M, Singh DP, Srivastava ON (2010) Biosynthesis of gold and silver nanoparticles by natural precursor clove and their functionalization with amine group. *J Nanopart Res* 12: 1667–1675.
20. Xie Y, Ye R, Liu H (2006) Biosurfactant rhamnolipid preparation of microemulsions. *Journal of Colloids and Surface.* 279: 175-178.
21. Blackwell M (2011) The fungi: 1, 2, and 3 ... 5.1 million species? *Am J Bot* 98: 426–438.
22. Sastry M, Ahmad A, Khan MI, Kumar R (2003) Biosynthesis of metal nanoparticles using fungi and Actinomycetes. *Curr Sci* 85: 162-170.
23. Govender Y, Riddin T, Gericke M, Whiteley CG (2009) Bioreduction of platinum salts into nanoparticles: A mechanistic perspective. *Biotechnol Lett* 31: 95-100.
24. Mohammadian A, Shaojaosadati SA, Rezee MH (2007) *Fusarium oxysporum* mediates photogeneration of silver nanoparticles. *Scientia Iranica* 14: 323-326.
25. Kumar SA, Abyaneh MK, Gosavi SW, Kulkarni SK, Pasricha R, et al. (2007) Nitrate reductase-mediated synthesis of silver nanoparticles from $AgNO_3$. *Biotechnol. Lett.* 29: 439-445.
26. Durán N, Marcato PD, Alves OL, De Souza GIH, Esposito E (2005) Mechanistic aspects of biosynthesis of silver nanoparticles by several *Fusarium oxysporum* strains. *J Nanobiotechnology.* 3: 1-8.
27. Ahmad A, Mukherjee P, Mandal D, Senapati S, Khan MI, et al. (2002) Enzyme mediated extracellular biosynthesis of CdS nanoparticles by the fungus *Fusarium oxysporum*. *JACS* 124: 12108-12109.
28. Bharde A, Rautray D, Bansal V, Ahmad A, Sarkar I, et al. (2006) Extracellular Biosynthesis of Magnetite using fungi. *Small* 2: 135-141.
29. Bansal V, Rautray D, Bharde A, Ahire K, Sanyal A, et al. (2005) Fungus-mediated biosynthesis of silica and Titania particles. *J Mater Chem.* 15: 2583-2589.
30. Bansal V, Rautray D, Ahamd A, Sastry M (2004) Biosynthesis of zirconia nanoparticles using the fungus *Fusarium oxysporum*. *J Mater Chem.* 14: 3303–3305.
31. Zhang X, He X, Wang K, Yang X (2011) Different active biomolecules involved in biosynthesis of gold nanoparticles by three fungus species. *J Biomed Nanotechnol.* 7: 245–254.
32. Mukherjee P, Senapati S, Mandal D, Ahmad A, Khan MI, et al. (2002) Extracellular synthesis of gold nanoparticles by the fungus *Fusarium oxysporum*. *Chem BioChem.* 3: 461–463.
33. Bansal V, Poddar P, Ahmad A, Sastry M (2006) Room-temperature biosynthesis of ferroelectric barium titanate nanoparticles. *J Am Chem Soc.* 128: 11958–11963.
34. Velmurugan P, Shim J, You Y, Choi S, Kamala-Kannan S, et al. (2010) Removal of zinc by live, dead, and dried biomass of *Fusarium* spp. isolated from the abandoned-metal mine in South Korea and its perspective of producing nanocrystals. *J Hazard Mater.* 182: 317–324.
35. Mukherjee P, Ahmad A, Mandal D, Senapati S, Sainkar SR, et al. (2001) Bioreduction of $AuCl_4$ ions by the fungus *Verticillium* sp and surface trapping of the gold nanoparticles formed. *Angew. Chem. Int. Ed.* 40: 3585-3588.
36. Mukherjee P, Ahmad A, Mandal D, Senapati S, Sainkar SR, et al. (2001) Fungus-mediated synthesis of silver nanoparticles and their immobilization in the mycelial matrix: a novel biological approach to nanoparticle synthesis. *Nano.* 1: 515-519.
37. Gericke M, Pinches A (2006) Microbial production of gold nanoparticles. *Gold Bull.* 239: 22-28.
38. Chen JC, Lin ZH, Ma XX (2003) Evidence of the production of silver nanoparticles via pretreatment of *Phoma* sp 32883 with silver nitrate. *Lett Appl Microbiol.* 37: 105-108.
39. Birla SS, Tiwari VV, Gade AK, Ingle AP, Yadav AP, et al. (2009) Fabrication of silver nanoparticles by *Phoma glomerata* and its combined effect against *Escherichia coli*, *Pseudomonas aeruginosa* and *Staphylococcus aureus*. *Lett Appl Microbiol.* 27: 76-83.
40. Shankar SS, Ahmad A, Pasricha R, Sastry M. (2003) Bioreduction of chloroaurate ions by *Geranium* leaves and its endophytic fungus yields gold nanoparticles of different shapes. *Journal of Material Chemistry* 13: 1822–1826. *Bioprocess Biosyst Eng.* 449: 224–230.
41. Sanghi R, Verma P (2009) Biomimetic synthesis and characterization of protein capped silver nanoparticles. *Bioresour Technol.* 100: 501–504.
42. Balaji DS, Basavaraja S, Deshpande R, Bedre D, Prabhakar BK, et al. (2009) Extracellular biosynthesis of functionalized silver nanoparticles by strains of *Cladosporium cladosporioides* fungus. *Colloids Surf. B.* 68: 88-92.
43. Ahmad A, Senapati S, Khan MI, Kumar, R Sastry M (2005) Extra-/intracellular biosynthesis of gold nanoparticles by an alkalotolerant fungus *Trichothecium* sp. *J. Biomed. Nanotechnol.* 1: 47-53.
44. Mukherjee P, Roy M, Mandal BP, Dey GK, Mukherjee PK, et al. (2008) Green synthesis of highly stabilized nanocrystalline silver particles by a non-pathogenic and agriculturally important fungus *asperellum*. *Nanotechnology.* 19: 103-110.
45. Bhainsa KC, De Souza SF (2006) Extracellular biosynthesis of silver nanoparticles using the fungus *Aspergillus fumigatus*. *Colloids Surf B.* 47: 160–164.
46. Raliya R, Tarafdar JC (2013) ZnO nanoparticle biosynthesis and its effect on phosphorous-mobilizing enzyme secretion and gum contents in Clusterbean (*Cyamopsis tetragonoloba* L.). *Agirc. Res* 2: 48–57.
47. Basavaraja S, Balaji SD, Lagashetty A, Rajasab AH, Venkataraman A (2007) Extracellular biosynthesis of silver nanoparticles using the fungus *Fusarium semitectum*. *Material Research Bulletin.* 43: 1164-1170.
48. Sawale BD, Salimath B, Deshpande R, Bedre MD, Prabhakar BK, et al. (2008) Biosynthesis and stabilization of Au and Au–Ag alloy nanoparticles by fungus, *Fusarium semitectum*. *Sci Tech Adv Mater* 9: 1.
49. Sawale BD, Salimath B, Deshpande R, Bedre MD, Prabhakar BK, et al. (2008) Biosynthesis and stabilization of Au and Au–Ag alloy nanoparticles by fungus, *Fusarium semitectum*. *Sci Tech Adv Mater.*
50. Rajakumar G, Rahuman A, Roopan SM, Khanna VG, Elango G, et al. (2012) Fungus-mediated biosynthesis and characterization of TiO_2 nanoparticles and

- their activity against pathogenic bacteria. *Spectrochim. Acta a Mol Biomol Spectrosc.* 91: 23-29.
51. Gade A, Bonde PP, Ingle AP, Marcato P, Duran N, et al. (2008) Exploitation of *Aspergillus niger* for synthesis of silver nanoparticles. *JBMB.* 2: 1-5.
52. Xie J, Lee JY, Wang DIC, Ting YP (2007) High-yield synthesis of complex gold nanostructures in a fungal system. *J Phys Chem. C* 111: 16858-16865.
53. Ingle A, Gade A, Pierrat S, Sonnichsen C, Rai M (2008) Mycosynthesis of silver nanoparticles using the fungus *F. acuminatum* and its activity against some human pathogenic bacteria. *Curr Nanosci.* 4: 141-144.
54. Sadowski Z, Maliszewska GB, Polowczyk I, Kozlecki T (2008) Synthesis of silver nanoparticles using microorganisms. *Mater Sci-Poland.* 26: 419-425.
55. Kumar SA, Peter YA, Nadaeu JL (2008) Facile biosynthesis, separation, conjugation of gold nanoparticles to doxorubicin. *Nanotechnology.*
56. Ingle A, Gade A, Bawaskar M, Rai MK (2009) *Fusarium solani*: A novel biological agent for the extracellular synthesis of silver nanoparticles. *J Nanopart Res.* 11: 2079-2085.
57. Raliya R (2013) Rapid, low-cost, and ecofriendly approach her for iron nanoparticle synthesis using *Aspergillus oryzae* TFR9. *J. Nanoparticles.*
58. Tarafdar JC, Raliya R, Rathore I (2012) Microbial synthesis of phosphorous nanoparticle from tri-calcium phosphate using *Aspergillus tubingensis* TFR-5. *J. Bionanosci* 6: 84-89.
59. Das SK, Das AR, Guha AK (2009) Gold nanoparticles: Microbial synthesis and application in water hygiene management. *Langmuir* 25: 8192-8199.
60. Sarkar J, Ray S, Chattopadhyay D, Laskar A, Acharya K (2012) Mycogenesis of gold nanoparticles using a phytopathogen *Alternaria alternata*. *Bioprocess Biosyst. Eng.* 35: 637-643.
61. Binupriya AR, Sathishkumar M, Yun SI (2010) Biocrystallization of silver and gold ions by inactive cell filtrate of *Rhizopus stolonifer*. *Colloids Surf B.* 79: 531-534.
62. Mishra A, Tripathy S, Wahab R, Jeong SH, Hwang I, et al. (2011) Microbial synthesis of gold nanoparticles using the fungus *Penicillium brevicompactum* and their cytotoxic effects against mouse mayo blast cancer $C_2C_1_2$ cells. *Appl. Microbiol Biotechnol.* 92: 617-630.
63. Narayanan KB, Sakthivel N (2011) Facile green synthesis of gold nanostructures by NADPH-dependent enzyme from the extract of *Sclerotium rolfsii*. *Colloids Surf. A Physicochem Eng Asp.* 380: 156-161.
64. Sanghi R, Verma P, Pouri S (2011) Enzymatic formation of gold nanoparticles using phanerochaete chrysosporium. *Sci. Res.* 1: 154-162.
65. Philip D (2009) Biosynthesis of Au, Ag and Au-Ag nanoparticles using edible mushroom extract. *Spectrochim Acta Part A* 73: 374-381.
66. Sanghi R, Verma P (2010) pH dependant fungal proteins in the "green" synthesis of gold nanoparticles. *Adv. Mater. Lett* 1: 193-199.
67. Chuhan A, Zubair S, Tufail S, Sherwani A, et al. (2011) Fungus-mediated biological synthesis of gold nanoparticles : Potential in detection of liver cancer. *Int J Nanomed* 6: 2305-2319.
68. Kathiresan K, Manivannan S, Nabeel AM, Dhivya B (2009) Studies on silver nanoparticles synthesized by a marine fungus *Penicillium fellutanum* isolated from coastal mangrove sediment. *Colloids Surf B* 71: 133-137.
69. Maliszewska I, Szewczyk K, Waszak K (2009) Biological synthesis of silver nanoparticles. *J Phys Conf Ser* 146.
70. Fayaz AM, Balaji K, Girilal M, Yadav R, Kalaichelvan PT, et al. (2009) Mycobased synthesis of silver nanoparticles and their incorporation into sodium alginate films for vegetable and fruit preservation. *J. Agric. Food Chem* 57: 6246-6252.
71. Fayaz AM, Balaji K, Girilal M, Yadav R, Kalaichelvan PT, et al. (2010) Biogenic synthesis of silver nanoparticles and their synergistic effect with antibiotics: A study against gram-positive and gram-negative bacteria. *Nanomed. Nanotechnol. Biol. Med* 6: 103-109.
72. Musarrat J, Dwivedi S, Singh BR, Al-Khedhairi AA, Azam A, et al. (2010) Production of antimicrobial silver nanoparticles in water extracts of the fungus *Amylomyces rouxii* strain KSU-09. *Bioresour Technol* 101: 8772-8776.
73. Saravanan M, Nanda A (2010) Extracellular synthesis of silver bionanoparticles from *Aspergillus clavatus* and its antimicrobial activity against MRSA and MRSE. *Colloids Surf. B Biointerfaces.* 77: 214-218.
74. Raliya R, Tarafdar JC (2012) Novel approach for silver nanoparticle synthesis using *Aspergillus terreus* CZR-1: mechanism perspective. *J. Bionano Sci* 6: 12-16.
75. Rai M, Yadav A, Gade A (2009) Silver nanoparticles as a new generation of antimicrobials. *Biotechnology Advances.* 27: 76-83.
76. Saha S, Sarkar J, Chattopadhyay D, Patra S, Chakraborty A, et al. (2010) Production of silver nanoparticles by a phytopathogenic fungus *Bipolaris nodulosa* and its antimicrobial activity. *Dig J Nanomater Bios.* 5: 887-895.