



Biodentine: A Promising Dentin substitute

Harpreet Singh*, Mandeep Kaur, Sheenam Markan and Pooja Kapoor

Department of conservative dentistry & Endodontics, Gian Sagar Dental College & Hospital, Patiala, Punjab, India

Abstract

Biodentine material has been recently introduced in dentistry in order to provide dentin substitute for coronal and radicular pulp. Although number of materials like Amalgam, GIC, Composite and MTA are available in market for repair of dentin loss in tooth structure, none of these possesses ideal properties. Despite of number of advantages of MTA, its limitations cannot be overlooked. These drawbacks have been overcome by a new calcium silicate based material named Biodentine which has good handling properties, short setting time and improved mechanical properties. In nut shell it is able to act as a promising dentin substitute in coronal and radicular portion of tooth.

Keywords: Biodentine; Dentin substitute; MTA; Perforation repair; Vital pulp therapy

Introduction

Loss of dentin is perhaps one of the major losses which hamper the integrity of the tooth structure to a significant extent. Whether be in the coronal portion or the radicular one, the dentin loss must be substituted with an artificial material, which can restore the physiological integrity of the tooth structure. From time immemorial, many materials have been studied for this purpose. While referring to the loss of dentin in the coronal part, such as in case of deep carious lesions, materials like Glass-Ionomer Cement have been used extensively, but with its limitation of not stimulating any reparative dentin formation on its own [1].

Similarly, in endodontic therapy, endodontic repair materials are being used, which ideally, should adhere to tooth structure; maintain a sufficient seal; be insoluble in tissue fluids; be dimensionally stable; non-resorbable, radiopaque and exhibit biocompatibility if not bioactivity. A number of materials have historically been used for retrograde filling and perforation repair such as amalgam, zinc-oxide-eugenol cement, composite resin, and glass-ionomer cement. Unfortunately, none of these materials have been able to satisfy the total requirements of an ideal material.

Mineral trioxide aggregate (MTA) is a biomaterial that has been investigated for applications in restorative dentistry since the early 1990s. Its multiple applications include: Direct & Indirect Pulp Capping, formation of apical plug, root end filling, perforation repair, furcation repair, repair of resorptive defects, management of immature apices (Apexogenesis/ Apexification) etc [2-7]. However, with usage, many limitations of this material have come into picture, such as difficulty in manipulation, longer setting time and cost factor.

Of late, Septodont's research group has developed a new class of dental material named Biodentine™ which could conciliate high mechanical properties with excellent biocompatibility as well as a bioactive behavior. Biodentine is the first all-in-one bioactive and biocompatible dentine substitute based on unique Active Biosilicate Technology™ and designed to treat damaged dentine both for restorative and endodontic purposes [8].

Like ProRoot MTA [3,4,9,10] and Portland's cement [11], it is a calcium-based cement. Compared to others calcium based cements, this material presents two advantages: i) a faster setting time of about 12 minutes and ii) higher mechanical properties. These physico-chemical properties associated with the biological behavior suggest that it may be used as a permanent dentine substitute [12].

Chemical Composition

Biodentine™ is conditioned in a capsule containing the good ratio of powder and liquid as shown in Table 1.

Properties of the different components:

- Tricalcium silicate ($3\text{CaO}\cdot\text{SiO}_2$): It is the main component of the powder. It regulates the setting reaction.
- Dicalcium silicate ($2\text{CaO}\cdot\text{SiO}_2$): It acts as second main core material
- Calcium carbonate (CaCO_3): It acts as filler.
- Zirconium dioxide (ZrO_2): It is added to provide the radio-opacity to the cement.
- Calcium chloride ($\text{CaCl}_2\cdot 2\text{H}_2\text{O}$): It is an accelerator [13].
- Water reducing agent (Superplasticiser): It is based on polycarboxylate but modified to obtain a high short-term resistance. It reduces the amount of water required by the mix (water / cement), decreases viscosity and improves handling of cement.

Active and collaborative research between Septodont and several universities for years led to a new calcium-silicate based formulation Biodentine™, which is suitable as a dentine replacement material whenever original dentine is damaged. The Active Biosilicate Technology™ is a proprietary technology developed according to the state-of-the-art pharmaceutical background applied to the high temperate ceramic mineral chemistry.

Powder	Liquid
Tricalcium silicate ($3\text{CaO}\cdot\text{SiO}_2$)	Calcium chloride ($\text{CaCl}_2\cdot 2\text{H}_2\text{O}$)
Dicalcium silicate ($2\text{CaO}\cdot\text{SiO}_2$)	Water reducing agent
Calcium carbonate (CaCO_3)	Water
Zirconium dioxide (ZrO_2)	
Iron oxide	

Table 1: Chemical composition of Biodentine.

*Corresponding author: Harpreet Singh, MDS, Associate Professor, Gian Sagar Dental College & Hospital, Patiala, Punjab, India, Tel: 9815493618; E-mail: hsgentledental@gmail.com

Received: June 24, 2014; Accepted: August 04, 2014; Published: August 11, 2014

Citation: Singh H, Kaur M, Markan S, Kapoor P (2014) Biodentine: A Promising Dentin substitute. J Interdiscipl Med Dent Sci 2: 140. doi: [10.4172/2376-032X.1000140](http://dx.doi.org/10.4172/2376-032X.1000140)

Copyright: © 2014 Singh H, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited

makes Biodentine™ particularly suitable in the endodontic indications of canal repair.

Resistance to acid

Concerning the durability of water based cements in the oral cavity, one of relevant characteristics of the dental materials is the resistance to acidic environment. It is known that glass ionomers have a tendency to erode under such conditions. The acid erosion and the effects of aging in artificial saliva on the Biodentine™ structure and composition were investigated by Laurent et al. [12]. They concluded that the erosion of Biodentine™ in acidic solution is limited and lower than for other water based cements (Glass Ionomers). In reconstituted saliva (containing phosphates), no erosion has been observed. Instead, a crystal deposition on the surface of Biodentine™ occurs, with an apatite-like structure. This deposition process due to a phosphate rich environment is very encouraging in terms of improvement of the interface between Biodentine™ and natural dentine. The deposition of apatitic structures might increase the marginal sealing of the material.

Adhesion

The mechanical adhesion of Biodentine™ cement to dental surfaces may result from a physical process of crystal growth within dentine tubules leading to a micromechanical anchor. The possible ion exchanges between the cement and dental tissues constitute an alternative hypothesis, or the two processes may well combine, eventually contributing to the adhesion of the cement, as it appears at the interface of Biodentine™ - adhesive systems.

Biodentine interfaces

The quality and durability of the interface is a key factor for the survival of a restorative material in clinical conditions. The marginal adaptation and the intimate contact with the surrounding materials (dentine, enamel, composites and other dental materials) are determinative features of its success. This was investigated by erosion in acid solutions, electron microscopy and microleakage tests. In the case of Biodentine™, the dissolution/precipitation process, which is inherent to the setting principle of calcium silicate cements, differentiates its interfacial behavior from the already known dental materials (composites, adhesives, glass ionomers).

Microleakage

The interfacial water tightness is an important parameter of the functionality and longevity of a restoration. The interface with dentine and enamel was examined using dye penetration methodology (silver nitrate), which is one of the most commonly used assays to assess, *in vitro*, the interfacial seal, by measuring the percolation of a dye along the different interfaces studied [26]. They concluded that Biodentine™ has a similar behavior in terms of leakage resistance as Fuji II LC at the interface with enamel, with dentine and with dentine bonding agents. Biodentine™ is then indicated in open sandwich class II restoration without any preliminary treatment. Biodentine exhibits low penetration at enamel/dentin interface.

Discoloration

Biodentine exhibits color stability over a period of 5 days and can serve as an alternative for use under light cure restorative materials in highly esthetic areas [27].

Biocompatibility

Laurent et al. [28], revealed that Biodentine is non-toxic and has

no adverse effects on cell differentiation and specific cell function. They reported that Biodentine increases TGF-B1 (growth factor) secretion from pulp cells which causes angiogenesis, recruitment of progenitor cells, cell differentiation and mineralization. The material is inorganic and non-metallic and can be used in direct and indirect pulp capping procedures as a single application dentin substitute without any cavity conditioning treatment.

Bioactivity

In both direct and indirect application, Biodentine does not seem to affect the target cells specific functions. About et al. [29] in 2005 investigated that Biodentine material is non-cytotoxic and non-genotoxic for pulp fibroblast at any concentration and stimulates dentin regeneration by inducing odontoblasts differentiation from pulp progenitor cells and promote mineralization, generating a reactionary dentine as well as a dense dentine bridge.

Antibacterial activity

Biodentine exhibits significant amount of antibacterial activity as well. Calcium hydroxide ions released from cement during setting phase of Biodentine increases pH to 12.5 which inhibits the growth of microorganisms and can disinfect the dentin.

Advantages of Biodentine

Amongst the wide range of advantages of this dentin substitute, the ones with clinical significance are:

- Reduced setting time
- Better handling & manipulation
- Improved mechanical properties
- Bioactivity of material

Uses/Clinical Applications of Biodentine

- It is used as a dentin substitute under a permanent restoration, and can be categorized as Indirect pulp capping material.
- It is used as a direct pulp capping material
- It can also be used in cases of partial pulpotomy.
- It has been advocated for use in performing Pulpotomy in primary molars
- It can be used for the Apexification procedure.
- It finds a significant application for repair of perforated root canals and/or pulp chamber floor
- Its use has also been advocated as a root end filling material

Applications of Biodentine in Restorative Dentistry

Use of Biodentine™ as a dentine substitute under a composite restoration

As stated by the manufacturer, Biodentine material can be used in class II fillings as a temporary enamel substitute and as permanent substitute in large carious lesions. A Study conducted by Septodont to compare the Biodentine with Filtek™ Z100 as posterior restorative material showed that Biodentine™ has easy handling, excellent anatomic form, very good marginal adaption and establishes a very good interproximal contact.

Stimulation of reactionary dentine in indirect pulp capping

Biodentine™ is able to stimulate a reactionary dentine which is a natural barrier against bacterial invasions. The reactionary dentine formation stabilizes at 3 months, indicating that the stimulation process is stopped when a sufficient dentine barrier is formed [30].

Use of Biodentine™ as a direct pulp capping material

Clinical trial conducted by Septodont showed that Biodentine™ can be used in direct pulp capping indications with a good success rate. Perard et al. [31] assessed the biological effects of Biodentine for use in pulp-capping treatment, on pseudo-odontoblastic and pulp cells and found that MTA and Biodentine modify the proliferation of pulp cell lines. Nowicka et al. [32] concluded that Biodentine had a similar efficacy to that of MTA in clinical setting and can be considered as alternative to MTA in pulp capping treatment because it preserves pulp vitality and promotes its healing.

Application in Endodontics

Use of Biodentine in pulpotomy

Villet et al. [33] performed partial pulpotomy in an immature premolar and detected fast tissue response (radiologically evident) by the dentin bridge formation and continuation of root development in shorter time. They experienced increased speed of pulpal response and homogenous bridge formation making Biodentine good choice than calcium hydroxide [34-36].

Use of Biodentine™ as an endodontic repair material

The endodontic indications of Biodentine™ are similar to the usual calcium silicate based materials, like the Portland cements and MTA. Biodentine has been recommended for perforation repair, formation of apical plug and furcation repair.

Biodentine™ is used as a root end filling material

The use of Biodentine as root end filling material has also been suggested. To evaluate, this application, Soundappan et al. [37] compared MTA, IRM and Biodentine as retrograde filling material and found that at 1mm level there was no difference among tested materials but at 2mm level MTA was superior to both IRM and Biodentine. The results reveal that further research is required before Biodentine can be advocated as root end filling material.

Advantages of Biodentine Over MTA

- Biodentine™ consistency is better suited to the clinical use than MTA.
- Biodentine™ presentation ensures a better handling and safety than MTA.
- Biodentine™ exhibits better mechanical properties than MTA.
- Biodentine™ does not require a two step restoration procedure as in the case of MTA.
- As the setting is faster, there is a lower risk of bacterial contamination than with MTA.

Conclusion

The good handling properties of Biodentine associated with its favorable biological, mechanical and physical properties indicate that material can be used efficiently in clinical practice as a pulp capping

agent and as an endodontic repair material. The easy handling and fast setting time are the major advantages in comparison to other similar materials available commercially. However, long term evaluation in clinical situations is required for further inferences.

Conflict of Interest

The authors declare that there is no conflict of interest regarding the publication of this paper.

References

1. Wilson AD, Kent BE (1972) A new translucent cement for dentistry. The glass ionomer cement. See comment in PubMed Commons below Br Dent J 132: 133-135.
2. Torabinejad M, Watson TF, Pitt Ford TR (1993) Sealing ability of a mineral trioxide aggregate when used as a root end filling material. See comment in PubMed Commons below J Endod 19: 591-595.
3. Torabinejad M, Hong CU, McDonald F, Pitt Ford TR (1995) Physical and chemical properties of a new root-end filling material. See comment in PubMed Commons below J Endod 21: 349-353.
4. Torabinejad M, Rastegar AF, Kettering JD, Pitt Ford TR (1995) Bacterial leakage of mineral trioxide aggregate as a root-end filling material. See comment in PubMed Commons below J Endod 21: 109-112.
5. Ford TR, Torabinejad M, Abedi HR, Bakland LK, Kariyawasam SP (1996) Using mineral trioxide aggregate as a pulp-capping material. See comment in PubMed Commons below J Am Dent Assoc 127: 1491-1494.
6. Torabinejad M, Hong CU, Pitt Ford TR, Kettering JD (1995) Cytotoxicity of four root end filling materials. See comment in PubMed Commons below J Endod 21: 489-492.
7. Torabinejad M, Pitt Ford TR, McKendry DJ, Abedi HR, Miller DA, et al. (1997) Histologic assessment of Mineral Trioxide aggregate as a rootend filing in monkeys. J Endodon 23: 225-228.
8. Septodont Biodentine™ Active Biosilicate Technology™. Scientific file 2010.
9. Camilleri J, Montesin FE, Brady K, Sweeney R, Curtis RV, et al. (2005) The constitution of mineral trioxide aggregate. See comment in PubMed Commons below Dent Mater 21: 297-303.
10. Lee SJ, Monsef M, Torabinejad M (1993) Sealing ability of a mineral trioxide aggregate for repair of lateral root perforations. See comment in PubMed Commons below J Endod 19: 541-544.
11. Camilleri J, Montesin FE, Curtis RV, Ford TR (2006) Characterization of Portland cement for use as a dental restorative material. See comment in PubMed Commons below Dent Mater 22: 569-575.
12. Laurent P, Camps J, De Méo M, Déjou J, About I (2008) Induction of specific cell responses to a Ca(3)SiO(5)-based posterior restorative material. See comment in PubMed Commons below Dent Mater 24: 1486-1494.
13. Chessmann CR, Asavapit S (1999) Effect of calcium chloride on the hydration and leaching of lead-retarded cement. Cement and Concrete Research 29: 885-892.
14. Taylor HFW (1997) Cement chemistry. (2nd edn), Thomas Telford Publishing, London.
15. Allen AJ, Thomas JJ, Jennings HM (2007) Composition and density of nanoscale calcium-silicate-hydrate in cement. See comment in PubMed Commons below Nat Mater 6: 311-316.
16. Garrault S, Behr T, Nonat A (2006) Formation of the C-S-H Layer during early hydration of tricalcium silicate grains with different sizes. See comment in PubMed Commons below J Phys Chem B 110: 270-275.
17. Andrale C, Blanco V, Collazo A, Keddam M, Novoa XR, et al. (1999) Cement paste hardening process studied by impedance spectroscopy. Electrochim Acta 44: 4314-4318.
18. Cabeza M, Keddam M, Novoa XR, Sanchez I, Takenouti H (2006) Impedance Spectroscopy to characterize the pore structure during the hardening process of Portland cement paste. Electrochim Acta 51: 1831-1841.
19. O'Brien W (2008) Dental Materials and their Selection.

20. Grech L, Mallia B, Camilleri J (2013) Investigation of the physical properties of tricalcium silicate cement-based root-end filling materials. See comment in PubMed Commons below Dent Mater 29: e20-28.
21. Koubi G, Colon P, Franquin JC, Hartmann A, Richard G, et al. (2013) Clinical evaluation of the performance and safety of a new dentine substitute, Biodentine, in the restoration of posterior teeth - a prospective study. See comment in PubMed Commons below Clin Oral Investig 17: 243-249.
22. Camilleri J (2013) Investigation of Biodentine as dentine replacement material. See comment in PubMed Commons below J Dent 41: 600-610.
23. Aggarwal V, Singla M, Miglani S, Kohli S (2013) Comparative evaluation of push-out bond strength of ProRoot MTA, Biodentine, and MTA Plus in furcation perforation repair. See comment in PubMed Commons below J Conserv Dent 16: 462-465.
24. Guneser MB, Akbulut MB, Eldeniz AU (2013) Effect of various endodontic irrigants on the push-out bond strength of biodentine and conventional root perforation repair materials. See comment in PubMed Commons below J Endod 39: 380-384.
25. Piconi C, Maccauro G (1999) Zirconia as a ceramic biomaterial. See comment in PubMed Commons below Biomaterials 20: 1-25.
26. Raskin A, Eschrich G, Dejou J, About I (2012) "In vitro microleakage of Biodentine as a dentin substitute compared to Fuji II LC in cervical lining restorations." The Journal of Adhesive Dentistry 14: 535-542.
27. Vallés M, Mercadé M, Duran-Sindreu F, Bourdelande JL, Roig M (2013) Influence of light and oxygen on the color stability of five calcium silicate-based materials. See comment in PubMed Commons below J Endod 39: 525-528.
28. Laurent P, Camps J, About I (2012) Biodentine(TM) induces TGF- β 1 release from human pulp cells and early dental pulp mineralization. See comment in PubMed Commons below Int Endod J 45: 439-448.
29. About I, Raskin A, Demeo M, Dejou J (2005) Cytotoxicity and genotoxicity of a new material for direct posterior fillings. abstract : European Cells and Materials.
30. Shayegan A, Jurysta C, Atash R, Petein M, Abbeele AV (2012) Biodentine used as a pulp-capping agent in primary pig teeth. See comment in PubMed Commons below Pediatr Dent 34: e202-208.
31. Pérard M, Le Clerc J, Watrin T, Meary F, Pérez F, et al. (2013) Spheroid model study comparing the biocompatibility of Biodentine and MTA. See comment in PubMed Commons below J Mater Sci Mater Med 24: 1527-1534.
32. Nowicka A, Lipski M, Parafiniuk M, Sporniak-Tutak K, Lichota D, et al. (2013) Response of human dental pulp capped with biodentine and mineral trioxide aggregate. See comment in PubMed Commons below J Endod 39: 743-747.
33. Villat C, Grosogeat, Seux D, Farge P (2013) Conservative approach of a symptomatic carious immature permanent tooth using a tricalcium silicate cement (Biodentine): a case report. Restorative Dentistry and Endodontics.
34. Luo Z, Li D2, Kohli MR3, Yu Q1, Kim S3, et al. (2014) Effect of Biodentine on the proliferation, migration and adhesion of human dental pulp stem cells. See comment in PubMed Commons below J Dent 42: 490-497.
35. Tran XV, Gorin C, Willig C, Barouk B, Pellat B, et al. (2012) Effect of a calcium-silicate-based restorative cement on pulp repair. See comment in PubMed Commons below J Dent Res 91: 1166-1171.
36. Zanini M, Sautier JM, Berdal A, Simon S (2012) Biodentine induces immortalized murine pulp cell differentiation into odontoblast-like cells and stimulates biomineralization. See comment in PubMed Commons below J Endod 38: 1220-1226.
37. Soundappan S, Sundaramurthy JL, Raghu S, Natanasabapathy V (2014) Biodentine versus Mineral Trioxide Aggregate versus Intermediate Restorative Material for Retrograde Root End Filling: An Invitro Study. See comment in PubMed Commons below J Dent (Tehran) 11: 143-149.

Citation: Singh H, Kaur M, Markan S, Kapoor P (2014) Biodentine: A Promising Dentin substitute. J Interdiscipl Med Dent Sci 2: 140. doi: 10.4172/2376-032X.1000140

Submit your next manuscript and get advantages of OMICS Group submissions

Unique features:

- User friendly/feasible website-translation of your paper to 50 world's leading languages
- Audio Version of published paper
- Digital articles to share and explore

Special features:

- 350 Open Access Journals
- 30,000 editorial team
- 21 days rapid review process
- Quality and quick editorial, review and publication processing
- Indexing at PubMed (partial), Scopus, EBSCO, Index Copernicus and Google Scholar etc
- Sharing Option: Social Networking Enabled
- Authors, Reviewers and Editors rewarded with online Scientific Credits
- Better discount for your subsequent articles

Submit your manuscript at: <http://www.scholarscentral.com/emssystem/>