

Biosensors Based on Plasmonics

Caiwang Ge^{1,2}, Yifei Tao¹ and Zhongyi Guo^{1*}¹School of Computer and Information, Hefei University of Technology, China²School of Electronics Science and Applied Physics, Hefei University of Technology, China

Abstract

Because of the sensitivity to refractive index changes, plasmonics nanostructures have been investigated broadly for the bio-molecules detection through the excitations of the propagating surface plasmon resonance (PSPR) or localized surface plasmon resonance (LSPR). PSPR sensors can detect sub-monolayer quantities of bio-molecules at the gold film surface and provide real-time data through continuous optical measurements. LSPR sensors could be more sensitive to local refractive index changes and the factors of nanoparticle material, shape and size are all interrelated and contribute to the refractive index sensitivities.

Keywords: PSPR sensors; LSPR sensors; Refractive index sensitivities; Bio-molecules detection

Introduction

Noble metal nanostructures display specific optical properties that arise from the coupling of incident light to the collective oscillation of the conduction electrons. The propagating surface plasmon resonance (PSPR) on a noble metal plate and localized surface plasmon resonance (LSPR) of a noble metal nanoparticle can be used for ultra-sensitive biosensors because changes in the refractive index near the metal surface cause a pronounced shift of the resonance wavelength [1]. Therefore, the modification (concentration) or absorption (species) of biological molecules on the metal nanostructures surface can be detected in a label-free manner using PSPR or LSPR spectra shifts.

PSPR sensors usually induce SPR on the noble metal surface through an optical prism. Meanwhile, SPR is a powerful surface analytical technique because it can detect sub-monolayer quantities of bio-molecules at the gold film surface and provide real-time data through continuous optical measurements [2]. Over the past years, a myriad of new structures with ever increasing sensitivities have been developed. The circular aperture-groove nanostructures patterned on a gold film can detect multiple binding events, which improves the sensing accuracy and high-throughput applications [3]. The sensitivity of the SPR based biosensor coated by a layer of graphene can be enhanced greatly compared to the conventional SPR biosensors [4]. In addition, PSPR shows a strong dependence on the angles of the incident light, which indicates that we can realize the concrete detection by scanning angles at a certain wavelength. Angular SPR sensors are also the most commonly used because of their wide linear ranges and high refractive index resolution. But for SPR sensors, there is one drawback of lacking a localized sensing volume.

In general, PSPR sensors are more sensitive than LSPR sensors to the changes in the bulk refractive index, i.e. the refractive index of the overall background medium, and LSPR sensors are more sensitive to local (the region near the nanoparticles) refractive index changes just in the vicinity of the nanoparticle because of an enormous enhancement of the optical local field in nanoscale [5]. Thus, LSPR sensors are suitable for bio-molecules, medical, cell research and environmental detection. For instance, if plasmonic nanoparticles are modified or adsorbed with small and subtle antibody molecules, they can work as immunosensors effectively. In addition, LSPR sensors save cost and are suitable for miniaturization, integrated with chips and rapid detection, because they require only a small volume and a simple optical configuration [6]. However, a relatively low sensitivity of LSPR sensors is a main reason

to restrict the applications in sensing. It is known that the sensitivity can be improved by a series of methods.

The vast majority of LSPR sensors have been carried out based on the Au or Ag nanoparticles. Gold is often chosen because of its chemical stability. The Ag particles are more desirable because they have sharper resonances and higher refractive index sensitivity [7]. Especially, in our previous work, we incorporated a suitable amount of gain material in core layer to improve the sensitivity of the gold-shell silica-core nanoparticle for bio-molecular sensors [8]. The gain-assisted sensors have the powerful ability to detect a subtle change in the concentration of its background medium. The particle shape also plays an important role in determining the sensitivity. In particular, it has been shown experimentally and in electromagnetic simulations that particles with sharp features or tips exhibit much higher refractive index sensitivities than that with smooth features [9,10]. For instance, the sensitivity of the nanorods could reach to 262 nm/RIU (refractive index unit), which was a significant improvement compared with that of the nanosphere [11]. And the Au star could obtain as high as 665 nm/RIU for the sensitivity of refractive index [12]. Meanwhile, the sharp tips could be used to increase the sensitivities further by producing a red shift in the plasmon resonance, and the sharp tips would also show an additional advantage for molecular detection at the microscopic level because a sharp tip creates an enormous enhancement of the optical local field. For metal nanoparticles with a given material and shape, the LSPR can be tailored by control of metal size in nanoscale, because the particle size has an important effect on the plasmon resonance wavelength, strength of the scattering cross-section and absorption and line width [13].

In conclusion, PSPR and LSPR sensors play a critical role in chemical and biological sensing technology. PSPR sensors can detect sub-monolayer quantities of analytes at the gold film surface. LSPR sensors could be more sensitive to local refractive index changes and are suitable for miniaturization, integrated with chips and rapid detection.

***Corresponding author:** Guo Z, School of Computer and Information, Hefei University of Technology, Hefei, 230009, China, Tel: 86 551 6290 10; E-mail: guozhongyi@hfut.edu.cn

Received July 30, 2015; Accepted August 28, 2015; Published August 31, 2015

Citation: Ge C, Tao Y, Guo Z (2015) Biosensors Based on Plasmonics. *Biosens J* 4: 123. doi:[10.4172/2090-4967.1000123](http://dx.doi.org/10.4172/2090-4967.1000123)

Copyright: © 2015 Ge C, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

References

1. Brolo AG (2012) Plasmonics for future biosensors. *Nat Photonics* 6: 709-713.
2. Ermini ML, Mariani S, Scarano S, Maria M (2014) Bioanalytical approaches for the detection of single nucleotide polymorphisms by Surface Plasmon Resonance biosensors. *Biosensors and Bioelectronics* 61: 28-37.
3. Zhao SS, Bukar N, Toulouse JL, Pelechacza D, Robitaille R, et al. (2015) Miniature multi-channel SPR instrument for methotrexate monitoring in clinical samples. *Biosensors and Bioelectronics* 64: 664-670.
4. Li P, Zhang B, Cui T (2015) Towards intrinsic graphene biosensor: A label-free, suspended single crystalline graphene sensor for multiplex lung cancer tumor markers detection. *Biosensors and Bioelectronics* 72: 168-174.
5. Mayer KM, Lee S, Liao H, Rostro BC, Fuentes A, et al. (2008) A label-free immunoassay based upon localized surface plasmon resonance of gold nanorods. *ACS Nano* 2: 687-692.
6. Yeo LY, Chang HC, Chan PPY, Friend JR (2011) Microfluidic devices for bioapplications. *Small* 7: 12-48.
7. Maier SA (2007) *Plasmonics: Fundamentals and Applications: Fundamentals and Applications*. Springer, New York.
8. Tao Y, Guo Z, Zhang A, Zhang J, Wang B, et al. (2015) Gold nanoshells with gain-assisted silica core for ultra-sensitive bio-molecular sensors. *Opt Commun* 349: 193-197.
9. Anker JN, Hall WP, Lyandres O, Shah NC, Zhao J, et al. (2008) Biosensing with plasmonic nanosensors. *Nature Materials* 7: 442-453.
10. Miller MM, Lazarides AA (2005) Sensitivity of metal nanoparticle surface plasmon resonance to the dielectric environment. *J Phys Chem B* 109: 21556-21565.
11. Nusz GJ, Marinakos SM, Curry AC, Dahlin A, Hook F, et al. (2008) Label-free plasmonic detection of biomolecular binding by a single gold nanorod. *Anal Chem* 80: 984-989.
12. Nehl CL, Liao H, Hafner JH (2006) Optical properties of star-shaped gold nanoparticles. *Nano letters* 6: 683-688.
13. Mayer KM, Hafner JH (2011) Localized surface plasmon resonance sensors. *Chemical reviews* 111: 3828-3857.

Citation: Ge C, Tao Y, Guo Z (2015) Biosensors Based on Plasmonics. Biosens J 4: 123. doi:10.4172/2090-4967.1000123

OMICS International: Publication Benefits & Features

Unique features:

- Increased global visibility of articles through worldwide distribution and indexing
- Showcasing recent research output in a timely and updated manner
- Special issues on the current trends of scientific research

Special features:

- 700 Open Access Journals
- 50,000 Editorial team
- Rapid review process
- Quality and quick editorial, review and publication processing
- Indexing at PubMed (partial), Scopus, EBSCO, Index Copernicus, Google Scholar etc.
- Sharing Option: Social Networking Enabled
- Authors, Reviewers and Editors rewarded with online Scientific Credits
- Better discount for your subsequent articles

Submit your manuscript at: <http://www.editorialmanager.com/lifesciences/default.aspx>