

Potential Application of Gold Nanostructures in Photodynamic Therapy

Hemant Kumar^{1*}, Arvind Kumar², Devendra Kumar Gangwar³, Prabin Kumar⁴, Gajendra Singh⁵ and Udit Soni⁶

¹University of Hyderabad, School of Chemistry, Hyderabad -500046, India

²Department of Zoology, Bareilly College Bareilly, Bareilly, M. J. P. Rohilkhand University, Bareilly-23001, India

³Department of Chemistry, Vardhaman College, M. J. P. Rohilkhand University, Bijnor-246701, India

⁴Department of Chemistry, Sri Guru Tegh Bahadur Khalsa College, University of Delhi, Delhi-07, India

⁵Department of Chemistry, Deshbandhu College, University of Delhi, Delhi-19, India

⁶Department of Biotechnology, Teri University, Vasant Kunj, New Delhi-70, India

Abstract

In this manuscript we report the synthesis of gold nanostructures (G_2) via seed-mediated growth method using CTAB as the surfactant, their size and morphology have been elucidated by TEM and DLS. The UV-visible absorption spectra of G_2 NPs showed a more intense peak at 680 nm and less intense peak at 520 nm indicating, formation of gold nanorods in majority. In case of G_2 nanostructures the longitudinal LSPR peak could be tunable as a function of their aspect ratio. The gold nanostructures conjugated with a photosensitizer (G_2 -PS NPs) were applied in Photodynamic Therapy (PDT). These G_2 -PS NPs stably-dispersed in aqueous medium and were characterized by optical studies. Cell viability studies demonstrated that only PS conjugated NPs (G_2 -PS NPs) could only generate cytotoxic singlet oxygen. The results indicate the promise of G_2 -PS NPs as delivery agents in photodynamic therapy.

Keywords: G_2 ; TEM; EDX; XRD; PDT

Introduction

Nanomedicine has progressed from being simple monodiagnostic or monotherapeutic platform to more complex applications such as multimodal diagnostics, externally activated therapy, and theranostic. Inorganic nanomaterials have played a major part in the latest developments owing to their stability, biological inertness, facile chemistry and certain unique properties at nanoscale.

The important aspect is the Light activated therapy which is also known as photodynamic therapy (PDT) is a noninvasively technique known for its minimal toxicity in the management and treatment of cancer and several non-malignant diseases [1-3]. It involves direct (topical) or systemic administration of a photosensitizer (PS) drug, which produces reactive singlet oxygen (1O_2) species when irradiated with light of appropriate wavelength (visible or NIR). The cytotoxic singlet oxygen is basically responsible for PDT effects. Due to the short half-life and limited diffusion distance (0.1 μ m) of singlet oxygen in aqueous media, PDT effect remains localized at the irradiated (diseased) site, avoiding damage to surrounding healthy cells/tissues [4-6]. Although conceptually straightforward, effective PDT process is fraught with several drawbacks. One of the major drawbacks is that most PS drugs are hydrophobic in nature, which limits their proper biodistribution and pharmacokinetics [7-10]. This drawback can be overcome if the PS drugs are attached with nanosized carriers for better aqueous dispersion and efficient PDT action. Thus both catalysis and light activated therapy are surface phenomenon associated with size and morphology of the nanostructures.

Herein, we have synthesized of G_2 NPs, conjugated with a PS molecule, and investigated whether nano-conjugation can enhance the singlet oxygen photogeneration efficacy of the PS. The PS molecule used here is 2-diazo-3-oxo-5, 10,15,20-tetraphenylchlorin [11-15].

Materials

Cetyltrimethylammonium bromide (CTAB), Hydrogen tetrachloroaurate(III) Trihydrate ($HAuCl_4 \cdot 3H_2O$), Silver nitrate ($AgNO_3$), L-ascorbic acid, Hydrochloric acid (HCl) solution (1.0

mol/L), Sodium borohydride ($NaBH_4$), were all purchased from Alfa Aesar, 2,9-dimethyl(1,10-phenanthroline), 3-(4,5-dimethylthiazol-2-yl), 5-diphenyltetrazolium bromide (MTT) reagent, fetal bovine serum (FBS), Phosphate buffer saline (PBS), Dulbecco's modified eagle's medium (DMEM), Penicillin/Streptomycin, and Amphotericin-B and 9,10-anthracenediyl-bis(methylene) Dimaleonic acid (ABMDMA) was purchased from Sigma-Aldrich.

Methods

Preparation of gold nanorods (G_2)

Synthesis of seed solution: The gold seeds were prepared as described by Nikoobakht et al. [15]. In a typical reaction, 10 mL aqueous solution of CTAB (0.1 M) was mixed with 200 μ L of aqueous gold precursor $HAuCl_4 \cdot 3H_2O$ (25 mM). Then, to this solution 600 μ L of ice-cold aqueous $NaBH_4$ solution (0.01 M) was quickly added. This leads to the controlled reduction of gold precursor into gold nanoseeds. After that, the seed solution was stirred for 2 minutes and kept at room temperature.

Seed mediated growth of G_2 : The nanogold growth solution was prepared by adding of 200 μ L $HAuCl_4 \cdot 3H_2O$ (25 mM) to 10 mL DDW containing 0.1 M CTAB. Then, 150 μ L ascorbic acid solution of (0.1 M), along with a specific amount of $AgNO_3$ and HCl were added to this solution separately. The amount of water was added to give a final mixture volume of 10 mL. In the final mixture, the concentrations of CTAB, $HAuCl_4$ and L-ascorbic acid were fixed at 0.1 M, 0.5 mM.

***Corresponding author:** Hemant Kumar, University of Hyderabad, School of Chemistry, Hyderabad -500046, India, Tel: 91403010500; E-mail: hemanatuh@gmail.com

Received December 13, 2015; **Accepted** January 06, 2016; **Published** January 25, 2016

Citation: Kumar H, Kumar A, Gangwar DK, Kumar P, Singh G, et al. (2016) Potential Application of Gold Nanostructures in Photodynamic Therapy. J Nanomed Nanotechnol 7: 349. doi:[10.4172/2157-7439.1000349](https://doi.org/10.4172/2157-7439.1000349)

Copyright: © 2016 Kumar H, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

The AgNO_3 concentration was varied from 0.06 mM and the HCl concentration from 0.01 M. The colorless growth solution was kept in a room temperature, after 30 minutes and 10 μL of seed solution was added to it. The resulting mixtures were left undisturbed for 20 min allowing seed-mediated GNPs formation to go to completion [12-14].

Formation of electrostatic conjugates of PS with G_2 (PS-G_2):

The PS-G_2 conjugates were formed by reaction of PS and G_2 with in aqueous phase. The positive charges on the surface of G_2 NPs were electrostatically-reacted with the negative charge present in PS. Here, 50 μL aqueous dispersion of PS (1 mg/mL) was added to a 1 mL of G_2 solution (10 mg/mL in H_2O), and mixed with shaking at room temperature for 2 minutes [3]. After formation of the PS-nanoparticle conjugates, they were separated from the free PS via centrifugation separation and washing in the aqueous medium.

Characterization

The sizes and morphology of nanostructures were determined via transmission electron microscopy (TEM) EDX and SAED using a TECNAI G2-30 U TWIN TEM instrument (FEI, Eindhoven, The Netherlands) with an acceleration voltage of 300 kV. The size of the nanostructures was further analyzed by dynamic light scattering (DLS) measurements, using a NANO-ZS series MALVERN ZETASIZER instrument. High resolution powder X-ray diffraction (XRD) was used to analyze the phase composition of the nanostructures, using a Bruker D8 Discover x-ray spectrometer, over the 2θ range from 20° – 75° at rate of 2.58/min, using Cu-K α radiation ($\lambda = 1.54060 \text{ \AA}$). The optical properties (UV-visible absorption and fluorescence emission spectra) of the gold nanostructures, drug, dye and photosensitizer samples were recorded using a Shimadzu UV-1601 spectrophotometer (Shimadzu, Kyoto, Japan) and a Cary Eclipse fluorescence spectrometer (Varian, Palo Alto, CA), respectively.

Detection of singlet oxygen generation by photosensitizer via photobleaching of ABMDMA

Photo-induced singlet oxygen generation was determined by photobleaching of the chemical probe 9, 10-anthracenediyl-bis (methylene) dimalonic acid (ABMDMA). ABMDMA is a water soluble derivative of anthracene that can be photobleached by singlet oxygen to its corresponding endoperoxide. The reaction was monitored spectrophotometrically by recording the decrease in optical density at 400 nm (corresponding to the absorption λ_{max} of ABMDMA). In a typical experiment, 0.40 μM of the sodium salt of ABMDMA in water was mixed with a mixture of photosensitizer (PS) and GNPs to give a final concentration of 2 μM for PS. The control experiment used 0.40 μM of the sodium salt of ABMDMA in water without any PS-GNPs mixture added. The solution was irradiated in an open quartz cuvette with continuous stirring. The absorbance measurements followed by irradiation were carried out every 10 min. A 450 W xenon-mercury lamp was used as the light source [15].

Results and Discussions

G_2 NPs were prepared using seed-mediated growth methods. The G_2 nanostructures have been synthesized in 20 nm diameter with some polydispersity, shown by TEM (Figure 1). XRD spectrum of gold nanostructures, showed diffraction peaks of 111, 200 and 220 (Figure 2), which match the characteristic peaks of inverse spinel oxide and the diffraction peaks delineate face-centered lattice (FCC) unit cells for the nanostructures (JCPDS 04-0785).

The UV-vis absorption spectra of aqueous dispersed G_2 shown in




Figure 1: TEM images of G_2 showing average at scale 20 nm gold nanostructures.




Figure 2: The powder X-ray diffraction of gold nanostructures.

Figures 3 and 4, corresponds to the LSPR phenomenon. Two peaks were observed for the G_2 , the first peak (transverse peak) at 520 nm, and the second one (longitudinal peak) at of 680 nm, which indicates that gold nanorods were formed as major component.

Use of the gold nanorods in PDT

Gold nanostructures can also be used as a drug carrier in photodynamic therapy (PDT) of cancer [15]. PDT occurs when photoexcited molecules (called photosensitizers or PS) transfer their excess energy to molecular oxygen, leading to the formation of highly toxic and reactive oxygen species (ROS) such as singlet oxygen which can kill cancer cells when targeted at cancer sites. The UV-vis spectra of PS was taken in water, which showed characteristic absorption peaks at 438, 525, 567, 605 and 669 nm.

We investigated the photogeneration of singlet oxygen by G_2 -PS NPs by studying the singlet oxygen mediated bleaching of the dye ABMDMA [15,16]. The reaction was studied by measuring the time dependent decrease in absorption of ABMDMA at 400 nm (λ_{max} for ABMDMA) (Figure 5). When absorption spectra of PS and ABMDMA were taken individually no change in λ_{max} were observed, when PS has been taken with ABMDMA down to 50% decrease in λ_{max} was observed, but with G_2 -PS NPs λ_{max} down to 30%. These absorption studies revealed that more cytotoxic singlet oxygen was generated with photosensitizer conjugated gold nanostructures and they can show promising therapeutic activity in light activated therapy (Figure 5).




Figure 3: The Absorbance spectra of gold nanostructures.




Figure 4: Absorbance spectra of PS in water solution (inset: expanded view of the long wavelength 'Q' bands of the PS).




Figure 5: Combined results for all the three systems, showing decrease of OD at 400 nm (absorption maxima of ABMDMA) as a function of laser irradiation time.




Figure 6: Percentage of cell survival of A-549 cells, after treatment with Placebo nanoparticles (G2 NPs), free PS (PS) and PS-Conjugated G2 nanoparticles (G2-PS NPs), with (light) and without (dark) subsequent irradiation with 630 nm laser light.

In vitro toxicity

For cell viability study human lung cancer cells A-549 grown in

DMEM media were used, supplemented with 10% fetal bovine serum (FBS), 1% antibiotic penicillin/streptomycin, and 1% antifungal amphotericin B. Approximate 1,50,000 cells/1 mL fresh media were added to each well of a sterilized 24-well plate to analyse cell viability upon treatment with various nanoparticles, and transferred back to the incubator and overnight growth, cells seeded in 24-well plates at a confluence of about 40%. The following samples were added per well in triplicates: (a) free PS (0.15 μ M), (b) G₂ NPs (25 μ g/ml), and (c) G₂-PS NPs (0.15 μ M PS conjugated on 25 μ g/ml of G₂ NPs). The two plates were then kept in incubator for 24 hours, then the cells were rinsed three times with sterile PBS and 500 μ L fresh medium per well was added. One of the plates was immediately kept in incubator (no light irradiation). The other plate was first exposed to a 635 nm laser light (10 mins in each well) using diode laser with output power of 20 mW, and then returned to the incubator. After further overnight incubation, their viability was analysed by the MTT method [16-18]. The experiment was carried out in triplicates. Results shown in Figure 6 revealed that G₂-PS killed upto 50% cancer cells on laser irradiation and without irradiation all cancer cells remains live, while G₂ and PS both did not affect the cancer cells with or without irradiation (Figure 6).

Conclusion

In this paper, we have discussed is microemulsion mediated process for the synthesis of gold nanostructures (G₂). Characterization methods such as TEM, XRD and absorption measurements confirmed the formation of G₂ nanostructures. The G₂ also have shown promise as drug carriers in PDT.

Acknowledgement

We are grateful to University of Hyderabad, School of Chemistry, for providing R&D Grant to support this study. We thank Dr. Udit Soni for their help related to research work. Grant number is RC/2015/9435 (DBC-304) financial supported.

References

- Triesscheijn M, Baas P, Schellens JH, Stewart FA (2006) Photodynamic therapy in oncology. *Oncologist* 11: 1034-1044.
- Qiang YG, Zhang XP, Li J, Huang Z (2006) Photodynamic therapy for malignant and non-malignant diseases: clinical investigation and application. *Chin Med J* 119: 845-857.
- Calzavara-Pinton PG, Venturini M, Sala RA (2005) Antimicrobial photodynamic therapy: an effective alternative approach to control fungal infections. *J Photochem Photobiol B* 78: 1-6.
- Dolmans DE, Fukumura D, Jain RK (2003) Photodynamic therapy for cancer. *Nat Rev Cancer* 3: 380-387.
- MacDonald IJ, Dougherty TJ (2001) Basic principles of photodynamic therapy. *J Porphyrins Phthalocyanines* 5: 105-129.
- Oleinick NL, Morris RL, Belichenko I (2002) The role of apoptosis in response to photodynamic therapy: what, where, why, and how. *Photochem Photobiol Sci* 1: 1-21.
- Kästle M, Grimm S, Nagel R, Breusing N, Grune T (2011) Combination of PDT and inhibitor treatment affects melanoma cells and spares keratinocytes. *Free Radic Biol Med* 50: 305-312.
- Charron G, Stuchinskaya T, Edwards R, Russell DA, Nann T (2012) Energy transfer in complexes of water-soluble quantum dots and chlorin e6 molecules in different environments. *J Phys Chem C* 116: 9334-9342.
- Hirakawa K, Hirano T, Nishimura Y, Arai T, Nosaka Y (2012) Relaxation Process of Photoexcited meso-Naphthylporphyrins while Interacting with DNA and Singlet Oxygen Generation. *J Phys Chem B* 116: 3037-3044.
- Cheng Y, Meyers JD, Broome AM, Kenney ME, Basilion JP, et al. (2011) Deep penetration of a PDT drug into tumors by noncovalent drug-gold nanoparticle conjugates. *J Am Chem Soc* 133: 2583-2591.
- Köpke T, Pink M, Zaleski JM (2006) A facile synthesis of 2-diazo-3-oxochlorins

- by lewis acid activation: selective modification of p-electron conjugated macrocycles. *Synlett* 14: 2183-2186.
12. Nikoobakht B, El-Sayed MA (2003) Preparation and Growth Mechanism of Gold Nanorods (NRs) Using Seed-Mediated Growth Method. *Chem Mater* 15: 1957-1962.
 13. Jana NR, Gearheart L, Murphy CJ (2001) Wet Chemical Synthesis of High Aspect Ratio Gold Nanorods. *J Phys Chem B* 105: 4065-4077.
 14. Zhu J, Yong KT, Roy I, Hu R, Ding H, et al. (2010) Additive controlled synthesis of gold nanorods (GNRs) for two-photon luminescence imaging of cancer cells. *Nanotechnology* 21: 285106.
 15. Roy I, Ohulchanskyy TY, Pudavar HE, Bergey EJ, Oseroff AR, et al. (2003) Ceramic-based nanoparticles entrapping water-insoluble photosensitizing anticancer drugs: a novel drug-carrier system for photodynamic therapy. *J Am Chem Soc* 125: 7860-7865.
 16. Ohulchanskyy TY, Roy I, Goswami LN, Chen Y, Bergey EJ, et al. (2007) Organically modified silica nanoparticles with covalently incorporated photosensitizer for photodynamic therapy of cancer. *Nano Lett* 7: 2835-2842.
 17. Roy I, Kumar P, Kumar R, Ohulchanskyy TY, Yong KT, et al. (2014) Ormosil nanoparticles as a sustained-release drug delivery vehicle. *RSC Advances* 4: 153498-53504.
 18. Kumar P, Roy AI (2014) optically and magnetically doped ormosil nanoparticles for bioimaging: Synthesis, characterization, and in vitro studies. *RSC Advances* 4: 16181-16186.

Citation: Kumar H, Kumar A, Gangwar DK, Kumar P, Singh G, et al. (2016) Potential Application of Gold Nanostructures in Photodynamic Therapy. J Nanomed Nanotechnol 7: 349. doi:[10.4172/2157-7439.1000349](https://doi.org/10.4172/2157-7439.1000349)

OMICS International: Publication Benefits & Features

Unique features:

- Increased global visibility of articles through worldwide distribution and indexing
- Showcasing recent research output in a timely and updated manner
- Special issues on the current trends of scientific research

Special features:

- 700 Open Access Journals
- 50,000 editorial team
- Rapid review process
- Quality and quick editorial, review and publication processing
- Indexing at PubMed (partial), Scopus, EBSCO, Index Copernicus and Google Scholar etc
- Sharing Option: Social Networking Enabled
- Authors, Reviewers and Editors rewarded with online Scientific Credits
- Better discount for your subsequent articles

Submit your manuscript at: www.editorialmanager.com/biochem