Journal of Materials Science and Nanomaterials

Cheng, J Mater Sci Nanomater 2023, 7:3

Short Communication Open Access

Synthesis of Low-Dimensional Copper-Based Nanomaterials: A Promising Avenue for Advanced Applications

Xin Cheng*

College of Material Science and Engineering, Beijing University of Chemical Technology, Beijing, 100029, PR China

Introduction

In recent years, the synthesis and exploration of low-dimensional nanomaterials have attracted significant attention due to their unique properties and potential applications in various fields. Among these nanomaterials, copper-based compounds have emerged as promising candidates, thanks to the remarkable physical, chemical, and electrical properties exhibited by copper. In this article, we delve into the synthesis techniques employed for fabricating low-dimensional copper-based nanomaterials and discuss their potential applications.

The synthesis of low-dimensional copper-based nanomaterials has emerged as a fascinating area of research, offering a plethora of opportunities for developing advanced materials with unique properties and diverse applications. Copper, a widely used metal known for its excellent electrical conductivity and catalytic properties, holds immense potential when engineered into low-dimensional nanoscale structures. These materials, with at least one dimension in the nanometer range, exhibit distinct properties compared to their bulk counterparts, making them highly attractive for a wide range of applications [1,2].

The synthesis of low-dimensional copper-based nanomaterials involves the precise control and manipulation of copper atoms or clusters to fabricate structures such as nanoparticles, nanowires, nanosheets, nanorods, and nanotubes. These nanomaterials possess enhanced properties due to quantum confinement effects, increased surface area, and altered electronic structure, opening up new avenues for scientific exploration and technological advancements [3,4].

To achieve the desired low-dimensional structures, various synthesis techniques have been developed, each offering unique advantages and control over the nanomaterial's size, shape, and composition. Chemical Vapor Deposition (CVD), solution-based methods, physical vapor deposition (PVD), and template-assisted synthesis are some of the commonly employed techniques in this field. These methods enable researchers to fabricate low-dimensional copper-based nanomaterials with tailored properties, ensuring their suitability for specific applications.

The unique properties exhibited by low-dimensional copper-based nanomaterials have propelled them into various scientific and technological domains. In electronics and optoelectronics, these materials have shown potential as transparent conductive films, flexible electronics, and high-performance transistors. Their excellent electrical conductivity, combined with optical transparency, makes them promising alternatives to conventional materials in these fields. Additionally, copper-based nanomaterials find applications in catalysis, energy storage, and sensing, where their enhanced catalytic activity, high surface area, and sensitivity to analytes offer remarkable performance enhancements [5].

This article aims to explore the synthesis techniques employed for fabricating low-dimensional copper-based nanomaterials and shed light on their potential applications. By understanding the synthesis strategies and the unique properties of these materials, researchers can continue to push the boundaries of nanoscience and unlock their full potential for advancements in various fields, ranging from electronics and energy storage to catalysis and sensing[6,7].

Description

Low-dimensional copper-based nanomaterials

Low-dimensional nanomaterials refer to materials with at least one dimension (length, width, or thickness) in the nanoscale range (typically less than 100 nanometers). Copper-based nanomaterials can exist in various forms, including nanoparticles, nanowires, nanosheets, nanorods, and nanotubes. These materials exhibit size-dependent properties that differ from their bulk counterparts, making them attractive for numerous applications in electronics, catalysis, energy storage, and sensing.

Synthesis techniques:

Several synthesis techniques have been developed to fabricate low-dimensional copper-based nanomaterials with precise control over size, shape, and composition. Some commonly employed techniques include:

a. Chemical vapor deposition (CVD): CVD involves the reaction of gaseous precursors on a heated substrate, leading to the deposition of copper-based nanomaterials. CVD allows for the growth of high-quality, large-area nanomaterials, such as copper nanowires and nanosheets.

b. Solution-based methods: Solution-based methods encompass various approaches, including solvothermal synthesis, hydrothermal synthesis, and chemical reduction. These methods involve the use of specific solvents, reducing agents, and templates to control the growth of copper-based nanomaterials in solution.

c. Physical vapor deposition (PVD): PVD techniques, such as sputtering and evaporation, involve the deposition of copper atoms or clusters onto a substrate under vacuum conditions. PVD enables the fabrication of thin films, nanowires, and other low-dimensional structures with excellent control over thickness and morphology [8].

d. Template-assisted synthesis: Template-assisted synthesis relies

***Corresponding author:** Xin Cheng, College of Material Science and Engineering, Beijing University of Chemical Technology, Beijing, 100029, PR China, E-mail: xicheng@mail.buct.edu.cn

Received: 01-May-2023, Manuscript No. JMSN-23-100663; **Editor assigned:** 04-May-2023, PreQC No. JMSN-23-100663 (PQ); **Reviewed:** 18-May-2023, QC No. JMSN-23-100663; **Revised:** 25-May-2023, Manuscript No. JMSN-23-100663 (R); **Published:** 31-May-2023, DOI: 10.4172/jmsn.100077

Citation: Cheng X (2023) Synthesis of Low-Dimensional Copper-Based Nanomaterials: A Promising Avenue for Advanced Applications. J Mater Sci Nanomater 7: 077.

Copyright: © 2023 Cheng X. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

on using pre-formed templates, such as porous membranes or sacrificial materials, to guide the growth of copper-based nanomaterials. This method offers precise control over the shape and size of the resulting nanomaterials [9].

Applications of low-dimensional copper-based nanomaterials

The unique properties exhibited by low-dimensional copper-based nanomaterials make them highly versatile for various applications:

a. Electronics and optoelectronics: Copper nanowires and nanosheets find applications in flexible electronics, transparent conductive films, and high-performance field-effect transistors. Their high electrical conductivity and optical transparency make them potential replacements for conventional indium tin oxide (ITO) in optoelectronic devices [10,11].

b. Catalysis: Copper nanoparticles and nanocomposites exhibit excellent catalytic activity, making them suitable for applications in catalytic reactions, such as hydrogenation, oxidation, and carbon dioxide reduction. These materials can serve as catalysts in energy conversion and environmental remediation processes.

c. Energy storage: Copper-based nanomaterials show promise in energy storage systems, including batteries, supercapacitors, and fuel cells. Their high surface area and electrical conductivity enhance charge transfer kinetics and improve overall device performance [12-15].

d. Sensing: Copper nanomaterials have been explored for sensing applications, such as gas sensors, biosensors, and environmental monitoring devices. Their large surface-to-volume ratio and sensitivity to various analytes make them effective transducers.

Discussion

The synthesis of low-dimensional copper-based nanomaterials has proven to be a promising avenue for the development of advanced materials with unique properties and diverse applications. Through precise control and manipulation of copper atoms or clusters, researchers have successfully fabricated various low-dimensional structures, including nanoparticles, nanowires, nanosheets, and nanotubes. These materials exhibit size-dependent properties that differ from their bulk counterparts, making them highly attractive for numerous scientific and technological applications.

Several synthesis techniques, such as Chemical Vapor Deposition (CVD), solution-based methods, Physical Vapor Deposition (PVD), and template-assisted synthesis, have been employed to fabricate low-dimensional copper-based nanomaterials with tailored properties. These techniques offer researchers the ability to control the size, shape, and composition of the nanomaterials, enabling precise engineering for specific applications.

The unique properties exhibited by low-dimensional copper-based nanomaterials have led to their utilization in various fields. In electronics and optoelectronics, these materials have shown promise as transparent conductive films, flexible electronics, and high-performance transistors. Their excellent electrical conductivity and optical transparency make them attractive alternatives to conventional materials. Moreover, copper-based nanomaterials find applications in catalysis, energy storage, and sensing. Their enhanced catalytic activity, large surface area, and sensitivity to analytes make them valuable in diverse areas, including energy conversion, environmental remediation, and biosensing.

As researchers continue to explore the synthesis techniques and properties of low-dimensional copper-based nanomaterials, further advancements are expected. Fine-tuning the synthesis processes and optimizing the materials' properties will unlock new possibilities for applications in various domains. Additionally, addressing challenges related to scalability, stability, and cost-effectiveness will facilitate their integration into commercial products and technologies.

Conclusion

The synthesis of low-dimensional copper-based nanomaterials holds tremendous potential for revolutionizing various industries. By harnessing their unique properties, researchers can pave the way for the development of innovative devices and systems with improved performance and efficiency. Continued research and exploration in this field will undoubtedly lead to exciting breakthroughs and contribute to advancements in electronics, catalysis, energy storage, sensing, and beyond.

Acknowledgement

None

Conflict of Interest

None

References

1. Hsiao CN, Chiou CS, Yang JR (2002) Aging reactions in a 17-4 PH stainless steel. Mater Chem Phys 74: 134-142.
2. Christien F, Telling MTF, Knight KS (2013) A comparison of dilatometry and in-situ neutron diffraction in tracking bulk phase transformations in a martensitic stainless steel. Mater Charact 82: 50-57.
3. Koistinen DP, Marburger RE (1959) A general equation prescribing the extent of the austenite-martensite transformation in pure iron-carbon alloys and plain carbon steels. Acta Metall 7: 59-60.
4. Facchini L (2010) Metastable austenite in 17-4 precipitation-hardening stainless steel produced by selective laser melting. Adv Eng Mater 12: 184-188.
5. Abbas T, Khan Y, Ahmed M, Anwar S (1992) X-ray diffraction study of the cation distribution in the Mn-Zn-ferrites. Solid State Commun 82: 701.
6. Schaefer M, Dietzmann G, Wirth H (1991) Magnetic losses in ferrites and nanocrystalline ribbons for power applications. J Magn Magn Mater 101: 95.
7. Rozman M, Drofenik M (1998) Sintering of nano sized Mn Zn ferrite powders. J Am Ceram Soc 81: 1757.
8. Chen SH, Chang Sc, Lin LN (2000) The influence of grain boundary internal stress on permeability: temperature curve for Mn–Zn ferrites. J Magn Magn Mater 209: 193.
9. Olsbye U (2012) Conversion of methanol to hydrocarbons: how zeolitecavity and pore size controls product selectivity. Angew Int Ed 51: 5810-5831.
10. Constales D, Yablonsky GS, Marin GB, Gleaves JT (2001) Multi-zone TAP-reactors theory and application: I. The global transfer matrix equation. Chem Eng Sci 56: 133-149.
11. Morgan K (2017) Forty years of temporal analysis of products. Catal Sci Technol 7: 2416-2439.
12. Gleaves JT, Yablonsky G, Zheng X, Fushimi R, Mills PL (2010) Temporal analysis of products (TAP)-Recent advances in technology forkinetic analysis of multi-component catalysts. J Mol Catal A Chem 315: 108-134.
13. Buchbinder D, Schleifenbaum H, Heidrich S, Bültmann J (2011) High power selective laser melting (HP SLM) of aluminum parts. Phys Procedia 12: 271-278.
14. Inokuti Y, Cantor B (1976) Splat-quenched Fe-Ni alloys. Scr Metall 10: 655-659.
15. Mercelis P, Kruth JP (2006) Residual stresses in selective laser sintering and selective laser melting. Rapid Prototyp J 12: 254-265.