

Stimuli Responsive Polymers for Biophysical Applications

Ajay Vidyasagar*

Department of Chemical Engineering and Materials Science, University of Minnesota, USA

Our quest to mimic biological functions using synthetic routes is an ongoing challenge that has shown immense potential in several biomedical applications. The potential of utilizing the smart behaviour of responsive polymers is wide open and has attracted the attentions of several leading researchers in the last two decades. Potential applications include and but limited are in drug delivery [1,2], biosensors [3], tissue engineering [4] and actuators [5]. The design of novel systems has to meet several criteria in order to become effective biomedical tools. They must be relatively simple to synthesize and deliver in vivo, exhibit specific responses tuned to targeted event of interest, be biocompatible/biodegradable and be cost effective.

Polymers that respond to specific stimuli by undergoing conformational or phase changes are of particular interest. The most widely studied synthetic smart responsive polymer is poly(N-isopropylacrylamide) (poly(NIPAAm)) which undergoes a reversible transition from a soluble hydrophilic coil state to an insoluble hydrophobic globule state at approximately 32°C in aqueous solutions [6-8]. The temperature at which the transition occurs is called the lower critical solution temperature (LCST), below which the polymer segments and solvent molecules co-exist as a single homogeneous phase with favourable free energy of mixing ($G < 0$). Above LCST, demixing occurs between the polymer segments and solvent molecules resulting in an increase in free energy ($G > 0$) due to phase separation. Other thermoresponsive polymers include poly(diethylacrylamide) (poly(DEAAm)) [9], Poly(N-vinylcaprolactone) (Poly(VCL)) [10] and poly(N-(dl)-(1-hydroxymethyl) propylmethacrylamide) (poly(dl)-HMPMA) [11], which all have a LCST in the range 32-37°C. The close proximity of the transitions to physiological temperatures makes these polymers ideal for several biological applications.

Like temperature, pH is an important environmental stimuli for biomedical applications. Some of the common pH responsive polymers like poly(acrylic acid) (PAA), Chitosan, poly(L-lysine) (PL), and poly(ethylene imine) (PEI) [12-14]. There are drastic changes to the pH environment from the gastrointestinal tract (pH-1.3) to the stomach (pH 5-8). The presence of ionization groups like amino or carboxyl groups offers pH sensitivity making them very desirable. Researchers usually combine thermo and pH responsiveness in order to design multi-responsive polymer systems. For example, NIPAAm copolymerized with acrylic acid and spirobenzopyran, provides temperature, pH and photo responsiveness [15]. In another example, colloidal particles have been used to design adhesion platforms for protein and specific cell types [16]. The possibilities of designing multi-responsive polymers are endless. There are however certain challenges owing to spatial restrictions that may occur especially at surfaces and interfaces of polymer gels or other similar systems. Another emerging area is to take advantage of biological compatibility with the synthetic versatility by designing hybrid polymers. For instance, poly(ethylene glycol) (PEG) segments have been conjugated with proteins to enhance biological activity [17]. In another example, poly(NIPAAm) conjugated to streptavidin engineered to present a thiol functionality by introducing a cysteine residue near a Biotin site. It was seen that Biotin reacts strongly by binding with the polymer-streptavidin conjugate below the LCST (<32°C) of NIPAAm. No evidence of such strong binding was seen above the LCST, owing to the phase transition

of the bioconjugate [18].

The design of stimuli responsive polymers in relatively a new and emerging area with infinite possibilities that need to be explored. The wide range of potential applications in biomedical fields such as in drug delivery, tissue engineering, surface activation, sensors, actuators etc. is only scratching the surface. Polymers that respond to single stimuli like temperature or pH alone are unlikely to find widespread applications. There is a need to fabricate materials that are truly smart with fine control over molecular weight, composition, and block architecture, incorporating multiple functionality within the polymer structures. The design of hybrid polymers that marry synthetic and biological features is the future of smart polymers for future biomedical applications. It is also imperative that researches focus on key areas like understanding the underlying molecular mechanism of designing better systems, improving mechanical robustness, improving specificity, and solving spatial constraints associated with confined systems.

References

1. Li SK, D'Emanuele A (2001) On-off transport through a thermoresponsive hydrogel composite membrane. *J Control Release* 75: 55-67.
2. Katono H, Maruyama A, Sanui K, Ogata N, Okano T, et al. (1991) Thermo-responsive swelling and drug release switching of interpenetrating polymer networks composed of poly(acrylamide-co-butyl methacrylate) and poly (acrylic acid). *J Control Release* 16: 215-228.
3. Holtz JH, Asher SA (1997) Polymerized colloidal crystal hydrogel films as intelligent chemical sensing materials. *Nature* 389: 829-832.
4. Lutolf MP, Lauer-Fields JL, Schmoekel HG, Metters AT, Weber FE, et al. (2003) Synthetic matrix metalloproteinase-sensitive hydrogels for the conduction of tissue regeneration: Engineering cell-invasion characteristics. *Proc National Acad Sci* 100: 5413-5418.
5. Hoffmann J, Plötner M, Kuckling D, Fischer WJ (1999) Photopatterning of thermally sensitive hydrogels useful for microactuators. *Sensors and Actuators A: Physical* 77: 139-144.
6. Schild HG (1992) Poly(N-isopropylacrylamide): experiment, theory and application. *Progress in Poly Sci* 17: 163-249.
7. Vidyasagar A, Smith HL, Majewski J, Toomey RG (2009) Continuous and discontinuous volume-phase transitions in surface-tethered, photo-crosslinked poly(N-isopropylacrylamide) networks. *Soft Matter* 5: 4733-4738.
8. Vidyasagar A, Majewski J, Toomey R (2008) Temperature Induced Volume-Phase Transitions in Surface-Tethered Poly(N-isopropylacrylamide) Networks. *Macromolecules* 41: 919-924.
9. Patra L, Vidyasagar A, Toomey R (2011) The effect of the Hofmeister series on the deswelling isotherms of poly(N-isopropylacrylamide) and poly(N,N-diethylacrylamide). *Soft Matter* 7: 6061-6067.

*Corresponding author: Ajay Vidyasagar, Department of Chemical Engineering and Materials Science, University of Minnesota, 421 Washington ave SE, Minneapolis, MN – 55455, USA, E-mail: avidyasa@umn.edu

Received December 05, 2013; Accepted December 08, 2013; Published December 11, 2013

Citation: Vidyasagar A (2013) Stimuli Responsive Polymers for Biophysical Applications. *J Phys Chem Biophys* 3: e116. doi:10.4172/2161-0398.1000e116

Copyright: © 2013 Vidyasagar A. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

10. Maeda Y, Nakamura T, Ikeda I (2001) Hydration and Phase Behavior of Poly(N-vinylcaprolactam) and Poly(N-vinylpyrrolidone) in Water. *Macromolecules* 35: 217-222.
11. Liu F, Urban MW, Jarrett WI (2007) Glass (T_g) and Stimuli-Responsive (TSR) Transitions in Random Copolymers. *Macromolecules* 41: 352-360.
12. Lee JW, Kim SY, Kim SS, Lee YM, Lee KH (1999) Synthesis and characteristics of interpenetrating polymer network hydrogel composed of chitosan and poly(acrylic acid). *J Appl Poly Sci* 73: 113-120.
13. Sideratou Z, Tsiourvas D, Paleos CM (1999) Quaternized Poly(propylene imine) Dendrimers as Novel pH-Sensitive Controlled-Release Systems. *Langmuir* 16: 1766-1769.
14. Burke SE, Barrett CJ (2003) pH-Responsive Properties of Multilayered Poly(L-lysine)/Hyaluronic Acid Surfaces. *Biomacromolecules* 4: 1773-1783.
15. Sumaru K, Kameda M, Kanamori T, Shinbo T (2004) Characteristic Phase Transition of Aqueous Solution of Poly(N-isopropylacrylamide) Functionalized with Spirobenzopyran. *Macromolecules* 37: 4949-4955.
16. Bae WS, Urban MW (2006) Lectin-Recognizable Colloidal Dispersions Stabilized by n-Dodecyl β -D-Maltoside: Particle-Particle and Particle-Surface Interactions. *Biomacromolecules* 7: 1156-1161.

Citation: Vidyasagar A (2013) Stimuli Responsive Polymers for Biophysical Applications. J Phys Chem Biophys 3: e116. doi:[10.4172/2161-0398.1000e116](https://doi.org/10.4172/2161-0398.1000e116)

Submit your next manuscript and get advantages of OMICS Group submissions

Unique features:

- User friendly/feasible website-translation of your paper to 50 world's leading languages
- Audio Version of published paper
- Digital articles to share and explore

Special features:

- 300 Open Access Journals
- 25,000 editorial team
- 21 days rapid review process
- Quality and quick editorial, review and publication processing
- Indexing at PubMed (partial), Scopus, DOAJ, EBSCO, Index Copernicus and Google Scholar etc
- Sharing Option: Social Networking Enabled
- Authors, Reviewers and Editors rewarded with online Scientific Credits
- Better discount for your subsequent articles

Submit your manuscripts as E- mail: www.omicsonline.org/submission/

